

## Kraton® G1702 H (SEP) DiBlock Copolymer

Category : Polymer , Thermoplastic , Elastomer, TPE

### Material Notes:

Description: Kraton G1702 H is a clear, linear diblock copolymer based on styrene and ethylene/propylene with a polystyrene content of 28%. It is supplied from North America in the physical form identified: Kraton G1702 HU - supplied as a powder. Region: Asia Pacific, Europe, Japan, North America, and South America Uses: Kraton G1702 H is used as an ingredient in formulating adhesives, sealants and coatings. It may also find use as a modifier of bitumen or thermoplastics and in compound formulations. Applications: Adhesives, Sealant and Coatings; Compounding and Personal Hygiene; Packaging and Polymod; and Personal Care

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kraton-G1702-H-SEP-DiBlock-Copolymer.php](http://www.lookpolymers.com/polymer_Kraton-G1702-H-SEP-DiBlock-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.910 g/cc	0.910 g/cc	ASTM D4025
Volatiles	<= 0.40 %	<= 0.40 %	KM 04
Kinematic Viscosity at 100°C (212°F)	18 - 22 cSt	18 - 22 cSt	1.23%; BAM 1201
Melt Flow	<= 1.0 g/10 min @Load 5.00 kg, Temperature 230 °C	<= 1.0 g/10 min @Load 11.0 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	41	41	10 seconds. Typical values on polymer compression molded at 350°F; ASTM D2240
Tensile Strength, Ultimate	2.068 MPa	299.9 psi	Typical properties based on film cast from toluene solution.; ASTM D412
Elongation at Break	<= 100 %	<= 100 %	Typical properties based on film cast from toluene solution.; ASTM D412

Chemical Properties	Metric	English	Comments
Diblock Content	100 %	100 %	

Descriptive Properties	Value	Comments
Content	Non-staining phenolic antioxidant	0.03-0.2%, KM 08
	Polystyrene	26.2-29%, KM 03, Measured on the polymer before hydrogenation
Styrene/Rubber Ratio	28/72	

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China