

Kuraray Genestar[®],ç GT2330 Nylon, 33% Glass Filled

Category : Polymer , Thermoplastic , Nylon

Material Notes:

Toughness V-0 Grade. It is well suited for components requiring a high strength in pin fitting process, due to high ductility properties.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kuraray-Genestar-GT2330-Nylon-33-Glass-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.58 g/cc	1.58 g/cc	
Water Absorption	1.0 %	1.0 %	
Linear Mold Shrinkage, Flow	0.0010 cm/cm	0.0010 in/in	
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	
Melt Flow	15 g/10 min @Load 2.16 kg, Temperature 320 Â°C	15 g/10 min @Load 4.76 lb, Temperature 608 Â°F	ASTM D1238
Spiral Flow	4.50 cm @Load 750 kg, Temperature 320 Â°C	1.77 in @Load 1650 lb, Temperature 608 Â°F	0.5mm diameter

Mechanical Properties	Metric	English	Comments
Tensile Strength	60.0 MPa	8700 psi	Weld; ASTM D638
	190 MPa	27600 psi	ASTM D638
Elongation at Yield	0.80 %	0.80 %	Weld; ASTM D638
	4.3 %	4.3 %	ASTM D638
Flexural Strength	240 MPa	34800 psi	ASTM D790
Flexural Modulus	10.0 GPa	1450 ksi	ASTM D790
Izod Impact, Notched	1.00 J/cm	1.87 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	306 Â°C	583 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	285 Â°C	545 Â°F	ASTM D648
Glass Transition Temp, Tg	125 Â°C	257 Â°F	

Flammability UL 94 Thermal Properties	V-0 Metric	V-0 English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Constant	3.4 @Frequency 1.00e+10 Hz	3.4 @Frequency 1.00e+10 Hz	ASTM D150
Dielectric Strength	30.0 kV/mm	762 kV/in	ASTM D149
Dielectric Loss Index	0.10 @Frequency 1.00e+10 Hz	0.10 @Frequency 1.00e+10 Hz	ASTM D150
Comparative Tracking Index	400 - 600 V	400 - 600 V	ASTM UL746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China