

## LATI Lapex A G/10 PES, 10% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Polyethersulfone (PES) , Polyethersulfone (PES), 10%Glass Fiber Filled

### Material Notes:

Polyether Sulfone (PES) based compound. Glass fibers. Low smoke density and low toxicity index. Very high dimensional stability. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LATI-Lapex-A-G10-PES-10-Glass-Fiber-Reinforced.php](http://www.lookpolymers.com/polymer_LATI-Lapex-A-G10-PES-10-Glass-Fiber-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in <sup>3</sup>	
Linear Mold Shrinkage, Flow	0.0040 - 0.0055 cm/cm	0.0040 - 0.0055 in/in	
Linear Mold Shrinkage, Transverse	0.0080 - 0.0095 cm/cm	0.0080 - 0.0095 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	70.0 MPa	10200 psi	
	@Temperature 150 Â°C	@Temperature 302 Â°F	
	75.0 MPa	10900 psi	
	@Temperature 120 Â°C	@Temperature 248 Â°F	
	90.0 MPa	13100 psi	
	@Temperature 90.0 Â°C	@Temperature 194 Â°F	
	95.0 MPa	13800 psi	
	@Temperature 60.0 Â°C	@Temperature 140 Â°F	
	100 MPa	14500 psi	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Elongation at Break	3.5 %	3.5 %	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
	3.7 %	3.7 %	
	@Temperature 60.0 Â°C	@Temperature 140 Â°F	
	4.1 %	4.1 %	

Mechanical Properties	Metric	English	Comments
	4.4 % @Temperature 90.0 Å°C	4.4 % @Temperature 194 Å°F	
	@Temperature 120 Å°C	@Temperature 248 Å°F	
	20 % @Temperature 150 Å°C	20 % @Temperature 302 Å°F	
Elongation at Yield	3.2 % @Temperature 150 Å°C	3.2 % @Temperature 302 Å°F	
Tensile Modulus	4.10 GPa @Temperature 150 Å°C	595 ksi @Temperature 302 Å°F	
	4.30 GPa @Temperature 120 Å°C	624 ksi @Temperature 248 Å°F	
	4.40 GPa @Temperature 90.0 Å°C	638 ksi @Temperature 194 Å°F	
	4.50 GPa @Temperature 60.0 Å°C	653 ksi @Temperature 140 Å°F	
	4.60 GPa @Temperature 23.0 Å°C	667 ksi @Temperature 73.4 Å°F	
Charpy Impact Unnotched	5.00 J/cmÅ²	23.8 ft-lb/inÅ²	
Charpy Impact, Notched	0.350 J/cmÅ²	1.67 ft-lb/inÅ²	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 Å°C	356 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	220 Å°C	428 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	215 Å°C	419 Å°F	
Vicat Softening Point	220 Å°C @Load 5.00 kg	428 Å°F @Load 11.0 lb	
Flammability, UL94	V-0 @Thickness 3.00 mm	V-0 @Thickness 0.118 in	
	V-0	V-0	

Thermal Properties	Metric @ Thickness 1.50 mm	English @ Thickness 0.0591 in	Comments
Oxygen Index	39 %	39 %	

Processing Properties	Metric	English	Comments
Melt Temperature	350 - 370 Â°C	662 - 698 Â°F	
Mold Temperature	140 - 165 Â°C	284 - 329 Â°F	
Drying Temperature	150 - 180 Â°C @Time 10800 sec	302 - 356 Â°F @Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China