

LATI Larton G/40 I6 PPS, 40% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) with 40% Glass Fiber Filler

Material Notes:

Polyphenylene Sulfide (PPS) based compound. Glass fibers. Good elongation. Very good chemical resistance. Very good thermal properties. Low smoke density and low toxicity index. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Larton-G40-I6-PPS-40-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.65 g/cc	0.0596 lb/in ³	
Linear Mold Shrinkage, Flow	0.0015 - 0.0045 cm/cm	0.0015 - 0.0045 in/in	
Linear Mold Shrinkage, Transverse	0.0070 - 0.011 cm/cm	0.0070 - 0.011 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	85.0 MPa	12300 psi	
	@Temperature 150 Â°C	@Temperature 302 Â°F	
	110 MPa	16000 psi	
	@Temperature 120 Â°C	@Temperature 248 Â°F	
	150 MPa	21800 psi	
	@Temperature 90.0 Â°C	@Temperature 194 Â°F	
	180 MPa	26100 psi	
	@Temperature 60.0 Â°C	@Temperature 140 Â°F	
	195 MPa	28300 psi	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Elongation at Break	1.7 %	1.7 %	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
	1.7 %	1.7 %	
	@Temperature 60.0 Â°C	@Temperature 140 Â°F	
	2.6 %	2.6 %	

Mechanical Properties	@Temperature 90.0 Metric °C	@Temperature 194 °F English	Comments
	3.0 %	3.0 %	
	@Temperature 120 °C	@Temperature 248 °F	
	3.3 %	3.3 %	
	@Temperature 150 °C	@Temperature 302 °F	
Tensile Modulus	6.00 GPa	870 ksi	
	@Temperature 150 °C	@Temperature 302 °F	
	9.20 GPa	1330 ksi	
	@Temperature 120 °C	@Temperature 248 °F	
	14.0 GPa	2030 ksi	
	@Temperature 90.0 °C	@Temperature 194 °F	
	14.5 GPa	2100 ksi	
	@Temperature 60.0 °C	@Temperature 140 °F	
	15.0 GPa	2180 ksi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	4.00 J/cm ²	19.0 ft-lb/in ²	
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	220 °C	428 °F	
Deflection Temperature at 0.46 MPa (66 psi)	280 °C	536 °F	
Deflection Temperature at 1.8 MPa (264 psi)	260 °C	500 °F	
Vicat Softening Point	260 °C	500 °F	
	@Load 5.00 kg	@Load 11.0 lb	
Flammability, UL94	V-0	V-0	
	@Thickness 3.00 mm	@Thickness 0.118 in	
	V-0	V-0	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	V-0	V-0	

Thermal Properties	Metric @ Thickness 0.750 mm	English @ Thickness 0.0295 in	Comments
Oxygen Index	44 %	44 %	
Glow Wire Test	960 Â°C @Thickness 1.00 mm	1760 Â°F @Thickness 0.0394 in	GWFI/GWT
	960 Â°C @Thickness 2.00 mm	1760 Â°F @Thickness 0.0787 in	GWFI/GWT

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	125 V	125 V	A solution

Processing Properties	Metric	English	Comments
Melt Temperature	290 - 310 Â°C	554 - 590 Â°F	
Mold Temperature	130 - 140 Â°C	266 - 284 Â°F	
Drying Temperature	130 - 150 Â°C	266 - 302 Â°F	
	@Time 10800 sec	@Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China