

## LATI Latan 13 POM

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

### Material Notes:

Polyoxymethylene (POM). Unfilled. Medium viscosity. Very good tribological properties. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America. Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LATI-Latan-13-POM.php](http://www.lookpolymers.com/polymer_LATI-Latan-13-POM.php)

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in <sup>3</sup>	
Linear Mold Shrinkage, Flow	0.020 - 0.023 cm/cm	0.020 - 0.023 in/in	
Linear Mold Shrinkage, Transverse	0.0205 - 0.0225 cm/cm	0.0205 - 0.0225 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	50.0 MPa	7250 psi	
Elongation at Break	40 %	40 %	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	>= 100 %	>= 100 %	
Elongation at Yield	@Temperature 60.0 °C	@Temperature 140 °F	
	>= 100 %	>= 100 %	
	@Temperature 90.0 °C	@Temperature 194 °F	
Tensile Modulus	0.850 GPa	123 ksi	
	@Temperature 90.0 °C	@Temperature 194 °F	
	1.30 GPa	189 ksi	
	@Temperature 60.0 °C	@Temperature 140 °F	
	2.20 GPa	319 ksi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	
Charpy Impact Unnotched			

Mechanical Properties	@Temperature 23.0 Metric °C	@Temperature 73.4 °F English °F	Comments
	NB	NB	
	@Temperature -20.0 °C	@Temperature -4.00 °F	
Charpy Impact, Notched	0.500 J/cm <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	0.700 J/cm <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	75.0 °C	167 °F	
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	
Deflection Temperature at 1.8 MPa (264 psi)	115 °C	239 °F	
Vicat Softening Point	150 °C	302 °F	
	@Load 5.00 kg	@Load 11.0 lb	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	600 V	600 V	A solution

Processing Properties	Metric	English	Comments
Melt Temperature	175 - 200 °C	347 - 392 °F	
Mold Temperature	70.0 - 90.0 °C	158 - 194 °F	
Drying Temperature	80.0 - 90.0 °C	176 - 194 °F	
	@Time 10800 sec	@Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China