

LATI Latigea B01 L/07 Bio-Polymer

Category : Polymer , Thermoplastic , Polylactic Acid (PLA) Biopolymer

Material Notes:

Bio-Polymer (PLA, PHB, ...) based compound. Wood flour. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America
Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Latigea-B01-L07-Bio-Polymer.php

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in ³	
Linear Mold Shrinkage, Flow	0.0015 - 0.0055 cm/cm	0.0015 - 0.0055 in/in	
Linear Mold Shrinkage, Transverse	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	
Elongation at Break	3.5 %	3.5 %	
Elongation at Yield	2.3 %	2.3 %	
Tensile Modulus	3.50 GPa	508 ksi	
Charpy Impact Unnotched	1.50 J/cm ²	7.14 ft-lb/in ²	
Charpy Impact, Notched	0.150 J/cm ²	0.714 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	55.0 Â°C	131 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	55.0 Â°C	131 Â°F	
Vicat Softening Point	60.0 Â°C @Load 5.00 kg	140 Â°F @Load 11.0 lb	

Processing Properties	Metric	English	Comments
Melt Temperature	170 - 190 Â°C	338 - 374 Â°F	
Mold Temperature	15.0 - 30.0 Â°C	59.0 - 86.0 Â°F	
Drying Temperature	40.0 - 50.0 Â°C @Time 21600 sec	104 - 122 Â°F @Time 6.00 hour	

Processing Properties	Metric	English	Comments
Descriptive Properties		Value	Comments
ISO Shrinkage - Pressure		60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China