

LATI Latilub 66-15T G/30 PA66, 30% Glass Fiber Reinforced, PTFE Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , Glass Fiber/PTFE Filled

Material Notes:

Self-lubricating product based on Polyamide 66 (PA66). PTFE. Glass fibers. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Latilub-66-15T-G30-PA66-30-Glass-Fiber-Reinforced-PTFE-Filled.php

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in ³	
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	
Linear Mold Shrinkage, Transverse	0.0090 - 0.012 cm/cm	0.0090 - 0.012 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	160 MPa	23200 psi	
Elongation at Break	2.5 %	2.5 %	
Tensile Modulus	9.50 GPa	1380 ksi	
Charpy Impact Unnotched	5.00 J/cm ²	23.8 ft-lb/in ²	
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	
Coefficient of Friction, Dynamic	0.25	0.25	
Coefficient of Friction, Static	0.30	0.30	
K (wear) Factor	19.0 x 10 ⁻⁸ mm ³ /N-M	9.43 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	260 Â°C	500 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	250 Â°C	482 Â°F	
Vicat Softening Point	250 Â°C @Load 5.00 kg	482 Â°F @Load 11.0 lb	

Processing Properties	Metric	English	Comments
Melt Temperature	275 - 300 Â°C	527 - 572 Â°F	

Mold Temperature Processing Properties	70.0 - 100 Â°C Metric	158 - 212 Â°F English	Comments
Drying Temperature	90.0 - 100 Â°C @Time 10800 sec	194 - 212 Â°F @Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China