

LG Chemical LC565 Polyolefin Elastomer for Polymer Modification

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Features: Improved impact strength in polypropylene; Excellent filler acceptance; Available as pellet form; Outstanding toughness with flexible performance; and Reduction of product weight
Application: General purpose thermoplastic elastomers, Polymer modification
CSA No. 25087-34-7
Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-LC565-Polyolefin-Elastomer-for-Polymer-Modification.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.875 g/cc	0.875 g/cc	ASTM D1505
Mooney Viscosity	8.0 @Temperature 121 Â°C	8.0 @Temperature 250 Â°F	1+4(121); ASTM D1646
Melt Flow	5.0 g/10 min @Load 2.16 kg, Temperature 190 Â°C	5.0 g/10 min @Load 4.76 lb, Temperature 374 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	54	54	ASTM D2240
Tensile Strength at Break	1.80 MPa	261 psi	ASTM D638
Elongation at Break	550 %	550 %	ASTM D638
1% Secant Modulus	8.04 MPa	1170 psi	ASTM D790
Tear Strength	20.0 kN/m	114 pli	Type C; ASTM D624

Thermal Properties	Metric	English	Comments
Melting Point	36.0 Â°C	96.8 Â°F	
Glass Transition Temp, Tg	-55.0 Â°C	-67.0 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China