

LG Chemical LUCEL FW700N Modified POM, Friction Resistance, Abrasion Resistance

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Feature: Injection Molding, Modified POM, Friction Resistance, Abrasion Resistance
 Application: Gears, Printer Roller Pumps, Gear Worm
 Wheels
 CAS No. 66455-31-0
 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-LUCEL-FW700N-Modified-POM-Friction-Resistance-Abrasion-Resistance.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 g/cc	1.39 g/cc	ASTM D792
Maximum Moisture Content	0.10	0.10	Injection Molding
Linear Mold Shrinkage, Flow	0.018 - 0.022 cm/cm @Thickness 3.20 mm	0.018 - 0.022 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	15 g/10 min @Load 2.16 kg, Temperature 190 Å°C	15 g/10 min @Load 4.76 lb, Temperature 374 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	53.7 MPa @Thickness 3.20 mm	7790 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	34 % @Thickness 3.20 mm	34 % @Thickness 0.126 in	50mm/min; ASTM D638
Flexural Yield Strength	70.3 MPa @Thickness 3.20 mm	10200 psi @Thickness 0.126 in	1.3mm/min; ASTM D790
Flexural Modulus	1.8061 GPa @Thickness 3.20 mm	261.95 ksi @Thickness 0.126 in	1.3mm/min; ASTM D790
Izod Impact, Notched	0.451 J/cm @Thickness 6.40 mm, Temperature 23.0 Å°C	0.845 ft-lb/in @Thickness 0.252 in, Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	93.0 Å°C @Thickness 6.40 mm	199 Å°F @Thickness 0.252 in	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	160 - 180 Â°C	320 - 356 Â°F	Injection Molding
Middle Barrel Temperature	170 - 190 Â°C	338 - 374 Â°F	Injection Molding
Front Barrel Temperature	180 - 200 Â°C	356 - 392 Â°F	Injection Molding
Nozzle Temperature	180 - 200 Â°C	356 - 392 Â°F	Injection Molding
Melt Temperature	200 - 220 Â°C	392 - 428 Â°F	Injection Molding
Mold Temperature	80.0 - 110 Â°C	176 - 230 Â°F	Injection Molding
Drying Temperature	90.0 - 110 Â°C	194 - 230 Â°F	Injection Molding
Dry Time	2.00 - 3.00 hour	2.00 - 3.00 hour	Injection Molding
Back Pressure	0.490 - 3.04 MPa	71.1 - 441 psi	Injection Molding
Screw Speed	50 - 100 rpm	50 - 100 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China