

## LG Chemical LUCEL HI515W POM+Rubber, High Impact

Category : Polymer , Thermoplastic , Acetal (POM)

### Material Notes:

Feature: Injection Molding, POM+Rubber, High Impact Application: Gears, Automobile Clip CAS No. 66455-31-0 and 155123-66-

3 Information provided by LG Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LG-Chemical-LUCEL-HI515W-POMRubber-High-Impact.php](http://www.lookpolymers.com/polymer_LG-Chemical-LUCEL-HI515W-POMRubber-High-Impact.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 g/cc	1.33 g/cc	ASTM D792
Maximum Moisture Content	0.10	0.10	Injection Molding
Linear Mold Shrinkage, Flow	0.017 - 0.020 cm/cm @Thickness 3.20 mm	0.017 - 0.020 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	9.0 g/10 min @Load 2.16 kg, Temperature 190 Å°C	9.0 g/10 min @Load 4.76 lb, Temperature 374 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	64	64	ASTM D785
Tensile Strength, Yield	41.9 MPa @Thickness 3.20 mm	6070 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	67 % @Thickness 3.20 mm	67 % @Thickness 0.126 in	50mm/min; ASTM D638
Flexural Yield Strength	47.3 MPa @Thickness 3.20 mm	6860 psi @Thickness 0.126 in	2.8mm/min; ASTM D790
Flexural Modulus	1.418 GPa @Thickness 3.20 mm	205.7 ksi @Thickness 0.126 in	2.8mm/min; ASTM D790
Izod Impact, Notched	0.726 J/cm @Thickness 6.40 mm, Temperature 23.0 Å°C	1.36 ft-lb/in @Thickness 0.252 in, Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	79.0 Å°C @Thickness 6.40 mm	174 Å°F @Thickness 0.252 in	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	160 - 180 Â°C	320 - 356 Â°F	Injection Molding
Middle Barrel Temperature	170 - 190 Â°C	338 - 374 Â°F	Injection Molding
Front Barrel Temperature	180 - 200 Â°C	356 - 392 Â°F	Injection Molding
Nozzle Temperature	180 - 200 Â°C	356 - 392 Â°F	Injection Molding
Melt Temperature	200 - 220 Â°C	392 - 428 Â°F	Injection Molding
Mold Temperature	80.0 - 110 Â°C	176 - 230 Â°F	Injection Molding
Drying Temperature	80.0 - 110 Â°C	176 - 230 Â°F	Injection Molding
Dry Time	2.00 - 3.00 hour	2.00 - 3.00 hour	Injection Molding
Back Pressure	0.490 - 3.04 MPa	71.1 - 441 psi	Injection Molding
Screw Speed	50 - 100 rpm	50 - 100 rpm	Injection Molding

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China