

LG Chemical LUMID GP2151BF PA66+GF15%, Flame Retardant

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Glass Fiber Filled

Material Notes:

Feature: Injection Molding, PA66+GF15%, Halogen Free Flame Retardant
 Application: Connectors
 CAS No. 32131-17-2, 25038-54-4, 65997-17-3, 88497-56-7, 1309-64-4 and 138265-88-0
 Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-LUMID-GP2151BF-PA66GF15-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	ASTM D792
Water Absorption	0.60 % @Temperature 23.0 Â°C, Time 86400 sec	0.60 % @Temperature 73.4 Â°F, Time 24.0 hour	ASTM D570
Maximum Moisture Content	0.090	0.090	Injection Molding
Linear Mold Shrinkage, Flow	0.0060 - 0.011 cm/cm @Thickness 3.20 mm	0.0060 - 0.011 in/in @Thickness 0.126 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Yield	123 MPa @Thickness 3.20 mm	17800 psi @Thickness 0.126 in	5mm/min; ASTM D638
Elongation at Break	3.0 % @Thickness 3.20 mm	3.0 % @Thickness 0.126 in	5mm/min; ASTM D638
Flexural Yield Strength	172 MPa @Thickness 3.20 mm	24900 psi @Thickness 0.126 in	1.3mm/min; ASTM D790
Flexural Modulus	6.57 GPa @Thickness 3.20 mm	953 ksi @Thickness 0.126 in	1.3mm/min; ASTM D790
Izod Impact, Notched	0.588 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	1.10 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	30.0 Âµm/m-Â°C	16.7 Âµin/in-Â°F	ASTM D696

Melting Point Thermal Properties	260 Å°C Metric	500 Å°F English	ASTM D3418 Comments
Deflection Temperature at 0.46 MPa (66 psi)	255 Å°C @Thickness 6.40 mm	491 Å°F @Thickness 0.252 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	240 Å°C @Thickness 6.40 mm	464 Å°F @Thickness 0.252 in	Unannealed; ASTM D648
UL RTI, Electrical	120 Å°C @Thickness >=0.750 mm	248 Å°F @Thickness >=0.0295 in	
	120 Å°C @Thickness >=1.50 mm	248 Å°F @Thickness >=0.0591 in	
	120 Å°C @Thickness >=3.00 mm	248 Å°F @Thickness >=0.118 in	
UL RTI, Mechanical with Impact	110 Å°C @Thickness >=0.750 mm	230 Å°F @Thickness >=0.0295 in	
	110 Å°C @Thickness >=1.50 mm	230 Å°F @Thickness >=0.0591 in	
	110 Å°C @Thickness >=3.00 mm	230 Å°F @Thickness >=0.118 in	
UL RTI, Mechanical without Impact	115 Å°C @Thickness >=0.750 mm	239 Å°F @Thickness >=0.0295 in	
	115 Å°C @Thickness >=1.50 mm	239 Å°F @Thickness >=0.0591 in	
	115 Å°C @Thickness >=3.00 mm	239 Å°F @Thickness >=0.118 in	
Flammability, UL94	V-0 @Thickness >=0.750 mm	V-0 @Thickness >=0.0295 in	
	V-0 @Thickness >=1.50 mm	V-0 @Thickness >=0.0591 in	

Thermal Properties	V-0 Metric	V-0 English	Comments
	@Thickness >=3.00 mm	@Thickness >=0.118 in	

Electrical Properties	Metric	English	Comments
Arc Resistance	0.00 - 60 sec	0.00 - 60 sec	ASTM D495
Comparative Tracking Index	250 - 400 V	250 - 400 V	
High Voltage Arc-Tracking Rate, HVTR	80.0 - 150 mm/min	3.15 - 5.91 in/min	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	265 - 275 Å°C	509 - 527 Å°F	Injection Molding
Middle Barrel Temperature	270 - 280 Å°C	518 - 536 Å°F	Injection Molding
Front Barrel Temperature	270 - 285 Å°C	518 - 545 Å°F	Injection Molding
Nozzle Temperature	270 - 280 Å°C	518 - 536 Å°F	Injection Molding
Melt Temperature	270 - 290 Å°C	518 - 554 Å°F	Injection Molding
Mold Temperature	80.0 - 110 Å°C	176 - 230 Å°F	Injection Molding
Drying Temperature	80.0 - 100 Å°C	176 - 212 Å°F	Injection Molding
Dry Time	4.00 - 5.00 hour	4.00 - 5.00 hour	Injection Molding
Back Pressure	29.4 - 58.8 MPa	4260 - 8530 psi	Injection Molding
Screw Speed	30 - 60 rpm	30 - 60 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China