

## LG Chemical LUPOL TE-5005H Thermoplastic Elastomer Alloy, Dimensional Stability

Category : Polymer , Thermoplastic , Elastomer, TPE

### Material Notes:

LUPOL resins, based on polyolefin with a wide range of characteristics, are a family of low cost engineering plastics. Applications: Automotive exterior parts. Information Provided by LG Chem

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LG-Chemical-LUPOL-TE-5005H-Thermoplastic-Elastomer-Alloy-Dimensional-Stability.php](http://www.lookpolymers.com/polymer_LG-Chemical-LUPOL-TE-5005H-Thermoplastic-Elastomer-Alloy-Dimensional-Stability.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.910 g/cc	0.910 g/cc	ASTM D792
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0080 cm/cm	0.0080 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	14.0 MPa	2030 psi	ASTM D638
Elongation at Break	>= 500 %	>= 500 %	ASTM D638
Flexural Strength	16.0 MPa	2320 psi	ASTM D790
Flexural Modulus	0.630 GPa	91.4 ksi	ASTM D790
Izod Impact, Notched	NB @Temperature 23.0 Â°C	NB @Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	95.0 Â°C	203 Â°F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	200 - 220 Â°C	392 - 428 Â°F	
Middle Barrel Temperature	200 - 230 Â°C	392 - 446 Â°F	
Front Barrel Temperature	210 - 230 Â°C	410 - 446 Â°F	
Nozzle Temperature	210 - 240 Â°C	410 - 464 Â°F	
Melt Temperature	210 - 240 Â°C	410 - 464 Â°F	
Mold Temperature	40.0 - 90.0 Â°C	104 - 194 Â°F	

Processing Properties	Metric	English	Comments
Drying Temperature	70.0 - 90.0 A°C	158 - 194 A°F	
Dry Time	2 - 3 hour	2 - 3 hour	
Injection Pressure	29.4 - 118 MPa	4260 - 17100 psi	First
	78.45 - 98.07 MPa	11380 - 14220 psi	Second
Back Pressure	0.490 - 3.92 MPa	71.1 - 569 psi	
Screw Speed	40 - 60 rpm	40 - 60 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China