

LG Chemical LUPOS HR2207A ABS+GF20%, General Purpose, Heat Resistance

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 20% Glass Fiber Filled , Acrylonitrile Butadiene Styrene (ABS), Heat Resistant, Molded

Material Notes:

Feature: Injection Molding, ABS+GF20%, General Purpose, Heat Resistance
Application: Electric & Electronic (Housing, Components)
Information provided by LG Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_LG-Chemical-LUPOS-HR2207A-ABSGF20-General-Purpose-Heat-Resistance.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	Injection Molding
Linear Mold Shrinkage, Flow	0.0020 - 0.0030 cm/cm @Thickness 3.20 mm	0.0020 - 0.0030 in/in @Thickness 0.126 in	ASTM D955
Melt Flow	2.0 g/10 min @Load 3.80 kg, Temperature 230 Â°C	2.0 g/10 min @Load 8.38 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	108 MPa @Thickness 3.20 mm	15600 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	2.5 % @Thickness 3.20 mm	2.5 % @Thickness 0.126 in	50mm/min; ASTM D638
Flexural Yield Strength	142 MPa @Thickness 3.20 mm	20600 psi @Thickness 0.126 in	10mm/min; ASTM D790
Flexural Modulus	6.86 GPa @Thickness 3.20 mm	996 ksi @Thickness 0.126 in	10mm/min; ASTM D790
Izod Impact, Notched	0.392 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	0.735 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	107 Â°C @Thickness 6.40 mm	225 Â°F @Thickness 0.252 in	Unannealed; ASTM D648

Thermal Properties	Metric	English	Comments
UL RTI, Electrical	50.0 Å°C @Thickness >=1.50 mm	122 Å°F @Thickness >=0.0591 in	
UL RTI, Mechanical with Impact	50.0 Å°C @Thickness >=1.50 mm	122 Å°F @Thickness >=0.0591 in	
UL RTI, Mechanical without Impact	50.0 Å°C @Thickness >=1.50 mm	122 Å°F @Thickness >=0.0591 in	
Flammability, UL94	HB @Thickness >=1.50 mm	HB @Thickness >=0.0591 in	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	220 - 235 Å°C	428 - 455 Å°F	Injection Molding
Middle Barrel Temperature	220 - 240 Å°C	428 - 464 Å°F	Injection Molding
Front Barrel Temperature	220 - 240 Å°C	428 - 464 Å°F	Injection Molding
Nozzle Temperature	230 - 245 Å°C	446 - 473 Å°F	Injection Molding
Melt Temperature	235 - 245 Å°C	455 - 473 Å°F	Injection Molding
Mold Temperature	50.0 - 80.0 Å°C	122 - 176 Å°F	Injection Molding
Drying Temperature	80.0 - 100 Å°C	176 - 212 Å°F	Injection Molding
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	Injection Molding
Back Pressure	0.981 - 3.92 MPa	142 - 569 psi	Injection Molding
Screw Speed	40 - 80 rpm	40 - 80 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China