

## LG Chemical Lupox<sup>®</sup> GP2156FT PBT+GF15%

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled

### Material Notes:

Description: Injection Molding, PBT+GF15%, Flame Retardant, High Flow  
 Application: IT/OA, E&E (Connector)  
 CAS No. 71342-77-3, 65997-17-3, 24968-12-5 and 1309-64-4  
 Information provided by LG Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LG-Chemical-Lupox-GP2156FT-PBTGF15.php](http://www.lookpolymers.com/polymer_LG-Chemical-Lupox-GP2156FT-PBTGF15.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.52 g/cc	1.52 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	Injection Molding
Linear Mold Shrinkage, Flow	0.0040 - 0.010 cm/cm @Thickness 3.20 mm	0.0040 - 0.010 in/in @Thickness 0.126 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	98.1 MPa @Thickness 3.20 mm	14200 psi @Thickness 0.126 in	50mm/min; ASTM D638
Elongation at Break	3.0 % @Thickness 3.20 mm	3.0 % @Thickness 0.126 in	5mm/min; ASTM D638
Flexural Yield Strength	147 MPa @Thickness 3.20 mm	21300 psi @Thickness 0.126 in	1.3mm/min; ASTM D790
Flexural Modulus	5.88 GPa @Thickness 3.20 mm	853 ksi @Thickness 0.126 in	1.3mm/min; ASTM D790
Izod Impact, Notched	0.539 J/cm @Thickness 3.20 mm, Temperature 23.0 Å°C	1.01 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	225 Å°C	437 Å°F	@ Break; ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	210 Å°C @Thickness 6.40 mm	410 Å°F @Thickness 0.252 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	200 Å°C @Thickness 6.40 mm	392 Å°F @Thickness 0.252 in	Unannealed; ASTM D648

Thermal Properties	130 Â°C Metric	266 Â°F English	Comments
UL RTI, Electrical	@Thickness >=0.710 mm	@Thickness >=0.0280 in	
	130 Â°C	266 Â°F	
	@Thickness >=1.50 mm	@Thickness >=0.0591 in	
	130 Â°C	266 Â°F	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
UL RTI, Mechanical with Impact	130 Â°C	266 Â°F	
	@Thickness >=0.710 mm	@Thickness >=0.0280 in	
	130 Â°C	266 Â°F	
	@Thickness >=1.50 mm	@Thickness >=0.0591 in	
	130 Â°C	266 Â°F	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
UL RTI, Mechanical without Impact	130 Â°C	266 Â°F	
	@Thickness >=0.710 mm	@Thickness >=0.0280 in	
	130 Â°C	266 Â°F	
	@Thickness >=1.50 mm	@Thickness >=0.0591 in	
	130 Â°C	266 Â°F	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
Flammability, UL94	V-0	V-0	
	@Thickness >=0.710 mm	@Thickness >=0.0280 in	
	V-0	V-0	
	@Thickness >=1.50 mm	@Thickness >=0.0591 in	
	V-0	V-0	
	@Thickness >=3.00 mm	@Thickness >=0.118 in	
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+17 ohm-cm	1.00e+17 ohm-cm	ASTM D257
	26.0 kV/mm	660 kV/in	

Dielectric Strength Electrical Properties	Metric @ Thickness 1.00 mm	English @ Thickness 0.0394 in	ASTM D149 Comments
Arc Resistance	0.00 - 60 sec	0.00 - 60 sec	ASTM D495
Comparative Tracking Index	175 V	175 V	Solution A; IEC 60112
Hot Wire Ignition, HWI	15 - 30 sec	15 - 30 sec	
	@Thickness >=0.710 mm	@Thickness >=0.0280 in	
	15 - 30 sec	15 - 30 sec	
	@Thickness >=1.50 mm	@Thickness >=0.0591 in	
	30 - 60 sec	30 - 60 sec	
	@Thickness >=3.30 mm	@Thickness >=0.130 in	
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	
	@Thickness 0.710 mm	@Thickness 0.0280 in	
	>= 120 arcs	>= 120 arcs	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	>= 120 arcs	>= 120 arcs	
	@Thickness 3.30 mm	@Thickness 0.130 in	
High Voltage Arc-Tracking Rate, HVTR	80.0 - 150 mm/min	3.15 - 5.91 in/min	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	235 - 250 Â°C	455 - 482 Â°F	Injection Molding
Middle Barrel Temperature	240 - 250 Â°C	464 - 482 Â°F	Injection Molding
Front Barrel Temperature	245 - 255 Â°C	473 - 491 Â°F	Injection Molding
Nozzle Temperature	245 - 255 Â°C	473 - 491 Â°F	Injection Molding
Melt Temperature	245 - 255 Â°C	473 - 491 Â°F	Injection Molding
Mold Temperature	60.0 - 100 Â°C	140 - 212 Â°F	Injection Molding
Drying Temperature	120 Â°C	248 Â°F	Injection Molding
Dry Time	4.00 - 5.00 hour	4.00 - 5.00 hour	Injection Molding

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China