

## LG Chemical SEETEC R3400 Polypropylene Random Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Impact Modified; Molded/Extruded

### Material Notes:

Features: Seetec R3400 is a polypropylene-ethylene random copolymer designed for non-transparent injection molding application.

SEETEC R3400 meets the FDA requirement in the code of Federal Regulations in 21 CFR 177.1520 for food contact.Applications: General

CPP Film and Non-Transparent Injection MoldingCAS No. 9010-79-1Information provided by LG Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LG-Chemical-SEETEC-R3400-Polypropylene-Random-Copolymer.php](http://www.lookpolymers.com/polymer_LG-Chemical-SEETEC-R3400-Polypropylene-Random-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.900 g/cc	0.900 g/cc	ASTM D1505
Melt Flow	8.0 g/10 min	8.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 Â°C	@Load 4.76 lb, Temperature 446 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	84	84	ASTM D785
Tensile Strength, Yield	26.5 MPa	3840 psi	50mm/min; ASTM D638
Elongation at Break	<= 500 %	<= 500 %	50mm/min; ASTM D638
Flexural Modulus	0.785 GPa	114 ksi	ASTM D760
Izod Impact, Notched	0.490 J/cm	0.918 ft-lb/in	ASTM D256
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Melting Point	130 - 170 Â°C	266 - 338 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	90.0 Â°C	194 Â°F	ASTM D648
Vicat Softening Point	135 Â°C	275 Â°F	ASTM D1525
	@Load 1.00 kg	@Load 2.20 lb	
Flash Point	>= 340 Â°C	>= 644 Â°F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215, Fengxian District, Shanghai City, China**