

Lanxess Pocan® B 1600 000000 PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Extrusion Grade , Polybutylene Terephthalate (PBT), Unreinforced, Molded

Material Notes:

PBT, non-reinforced, injection molding, extrusion, food contact

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lanxess-Pocan-B-1600-000000-PBT.php

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in ³	ISO 1183
Water Absorption	0.50 %	0.50 %	Test Sim. to ISO 62
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23°C/50% R.H.; Test Sim. to ISO 62
Viscosity Test	140 cm ³ /g	140 cm ³ /g	Viscosity number; ISO 307, 1157, 1628
Melt Flow	18 g/10 min @Load 2.16 kg, Temperature 260 °C	18 g/10 min @Load 4.76 lb, Temperature 500 °F	Estimated using room temperature density; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.0 MPa	7980 psi	ISO 527-1/-2
Elongation at Break	>= 50 %	>= 50 %	Nominal; ISO 527-1/-2
Elongation at Yield	4.0 %	4.0 %	ISO 527-1/-2
Tensile Modulus	2.60 GPa	377 ksi	ISO 527-1/-2
Charpy Impact Unnotched	20.0 J/cm ²	95.2 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	<= 1.00 J/cm ²	<= 4.76 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	<= 1.00 J/cm ²	<= 4.76 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Impact	3706	3706	Puncture maximum force (N); ISO 6603-2
	4275	4275	
			Puncture maximum force (N); ISO

Mechanical Properties	Metric @Temperature -30.0 °C	English @Temperature -22.0 °F	6603-2 Comments
Puncture Energy	44.0 J	32.5 ft-lb	ISO 6603-2
	23.0 J @Temperature -30.0 °C	17.0 ft-lb @Temperature -22.0 °F	ISO 6603-2
Tensile Creep Modulus, 1 hour	2200 MPa	319000 psi	ISO 899-1
Tensile Creep Modulus, 1000 hours	1300 MPa	189000 psi	ISO 899-1

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	120 µm/m-°C	66.7 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	130 µm/m-°C	72.2 µin/in-°F	ISO 11359-1/-2
Melting Point	225 °C	437 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	60.0 °C	140 °F	ISO 75-1/-2
Deflection Temperature at 8.0 MPa	45.0 °C	113 °F	ISO 75-1/-2
Vicat Softening Point	180 °C	356 °F	50°C/h 50N; ISO 306
Flammability, UL94	HB @Thickness 0.800 mm	HB @Thickness 0.0315 in	IEC 60695-11-10
	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	IEC 60695-11-10
Oxygen Index	24 %	24 %	ISO 4589-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	IEC 60093
Dielectric Constant	3.2 @Frequency 1.00e+6 Hz	3.2 @Frequency 1.00e+6 Hz	IEC 60250
	3.4 @Frequency 100 Hz	3.4 @Frequency 100 Hz	IEC 60250
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 60243-1

Electrical Properties	Metric	English	Comments
Dissipation Factor	@Frequency 100 Hz	@Frequency 100 Hz	IEC 60250
	0.020	0.020	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	600 V	600 V	IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	260 °C	500 °F	Injection Molding; ISO 294
Mold Temperature	80.0 °C	176 °F	Injection Molding; ISO 10724

Descriptive Properties	Value	Comments
Form	Pellets	
ISO Shortname	ISO 7792-1-PBT,G,11-030	
Processing	Film extrusion	
	Injection molding	
	Other extrusion	
	Profile extrusion	
	Sheet extrusion	
Region	Asia Pacific	
	Europe	
	Near East/Africa	
	North America	
	South and Central America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China