

Lehmann & Voss LUVOCOM[®] 1-1119-1 Polyamide 66, with carbon fiber, heat stabilized

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Carbon Fiber Filled

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. High-strength and high-stiff parts; low coefficient of expansion. Reduced moment of inertia compared with metal parts. Electrically conductive, suitable for continuous discharging of statically generated electricity. Gear parts for automotive appliances, control disks, cams, sliding elements. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1-1119-1-Polyamide-66-with-carbon-fiber-heat-stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ISO 1183
Water Absorption	<= 1.0 %	<= 1.0 %	23 [°] C/24h
Linear Mold Shrinkage	0.0010 - 0.0050 cm/cm	0.0010 - 0.0050 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	190 MPa	27600 psi	
Elongation at Yield	3.5 %	3.5 %	
	3.8 %	3.8 %	flexural
Modulus of Elasticity	15.0 GPa	2180 ksi	
Flexural Strength	300 MPa	43500 psi	
Flexural Modulus	13.0 GPa	1890 ksi	
Charpy Impact Unnotched	6.50 J/cm ²	30.9 ft-lb/in ²	edgewise; ISO 179 1eU
	6.00 J/cm ²	28.6 ft-lb/in ²	ISO 179
	@Temperature -30.0 [°] C	@Temperature -22.0 [°] F	
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179 1eA
Coefficient of Friction, Dynamic	0.22	0.22	
Coefficient of Friction, Static	0.17	0.17	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	120 [°] C	248 [°] F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	240 Â°C	464 Â°F	
Vicat Softening Point	245 Â°C	473 Â°F	DIN ISO 306

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 1000 ohm	<= 1000 ohm	
Insulation Resistance	<= 10000 ohm	<= 10000 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	290 Â°C	554 Â°F	mass temp
Nozzle Temperature	280 - 300 Â°C	536 - 572 Â°F	
Zone 1	290 - 310 Â°C	554 - 590 Â°F	
Zone 2	290 - 310 Â°C	554 - 590 Â°F	
Zone 3	290 - 310 Â°C	554 - 590 Â°F	
Mold Temperature	90.0 - 120 Â°C	194 - 248 Â°F	
Drying Temperature	75.0 Â°C @Time 21600 - 57600 sec	167 Â°F @Time 6.00 - 16.0 hour	Dehumidifying dryer
	105 Â°C @Time 14400 - 21600 sec	221 Â°F @Time 4.00 - 6.00 hour	Vacuum Dryer

Descriptive Properties	Value	Comments
Color	natural color (black)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China