

## Lehmann & Voss LUVOCOM<sup>®</sup> 1-7488 Polyamide 66, with carbon fiber, heat stabilized

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Carbon Fiber Filled

### Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. High-strength and high-stiff parts; low coefficient of expansion. Reduced moment of inertia compared with metal parts. Electrically conductive, suitable for continuous discharging of statically generated electricity. High dimensionally stable precision parts with low warpage and narrow tolerance range. Gear parts for automotive appliances, control disks, cams, sliding elements. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lehmann-Voss-LUVOCOM-1-7488-Polyamide-66-with-carbon-fiber-heat-stabilized.php](http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1-7488-Polyamide-66-with-carbon-fiber-heat-stabilized.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.38 g/cc	1.38 g/cc	ISO 1183
Water Absorption	<= 1.0 %	<= 1.0 %	23Â°C/24h
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	255 MPa	37000 psi	
Elongation at Yield	1.9 %	1.9 %	
	2.5 %	2.5 %	flexural
Modulus of Elasticity	32.0 GPa	4640 ksi	
Flexural Strength	380 MPa	55100 psi	
Flexural Modulus	27.0 GPa	3920 ksi	
Charpy Impact Unnotched	4.50 J/cm <sup>2</sup>	21.4 ft-lb/in <sup>2</sup>	flatwise; ISO 179 1fU

Thermal Properties	Metric	English	Comments
CTE, linear	14.0 Âµm/m-Â°C	7.78 Âµin/in-Â°F	DIN 53752
Maximum Service Temperature, Air	120 Â°C	248 Â°F	
	160 Â°C	320 Â°F	short term
Flammability, UL94	HB	HB	not recognized by UL

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 100 ohm	<= 100 ohm	

Electrical Properties	Metric	English	Comments
Insulation Resistance	≥ 1000 ohm	≥ 1000 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	290 Â°C	554 Â°F	mass temp
Nozzle Temperature	280 - 300 Â°C	536 - 572 Â°F	
Zone 1	290 - 310 Â°C	554 - 590 Â°F	
Zone 2	290 - 310 Â°C	554 - 590 Â°F	
Zone 3	290 - 310 Â°C	554 - 590 Â°F	
Mold Temperature	90.0 - 120 Â°C	194 - 248 Â°F	
Drying Temperature	75.0 Â°C @Time 21600 - 57600 sec	167 Â°F @Time 6.00 - 16.0 hour	Dehumidifying dryer
	105 Â°C @Time 14400 - 21600 sec	221 Â°F @Time 4.00 - 6.00 hour	Vacuum Dryer

Descriptive Properties	Value	Comments
Color	natural color (black)	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China