

Lehmann & Voss LUVOCOM® 1301-7767 PPS, linear, with carbon fiber, lubricant modified

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) with 10% Carbon Fiber Filler

Material Notes:

Applications: Automotive industry, textile-and office machinery, medical- and precision engineering.High continuous use and heat distortion temperature. Non flammable.Strong, stiff parts.Suitable for metall inserts.Improved friction and wear behaviour. Emergency running property.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-1301-7767-PPS-linear-with-carbon-fiber-lubricant-modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.62 g/cc	1.62 g/cc	ISO 1183
Water Absorption	<= 0.050 %	<= 0.050 %	23Â°C/24h
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	115 MPa	16700 psi	
Elongation at Yield	1.0 %	1.0 %	
	1.35 %	1.35 %	flexural
Modulus of Elasticity	13.0 GPa	1890 ksi	
Flexural Strength	160 MPa	23200 psi	
Flexural Modulus	11.0 GPa	1600 ksi	
Charpy Impact Unnotched	1.40 J/cmÂ²	6.66 ft-lb/inÂ²	flatwise; ISO 179 1fU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	220 Â°C	428 Â°F	
	240 Â°C	464 Â°F	short term

Electrical Properties	Metric	English	Comments
Insulation Resistance	<= 1.00e+6 ohm	<= 1.00e+6 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	330 Â°C	626 Â°F	mass temp

Processing Properties	Metric	English	Comments
Zone 1	300 - 320 Å°C	572 - 608 Å°F	
Zone 2	310 - 330 Å°C	590 - 626 Å°F	
Zone 3	320 - 340 Å°C	608 - 644 Å°F	
Mold Temperature	150 - 180 Å°C	302 - 356 Å°F	
Drying Temperature	50.0 - 90.0 Å°C	122 - 194 Å°F	
	@Time >= 14400 sec	@Time >= 4.00 hour	
	100 - 140 Å°C	212 - 284 Å°F	Dehumidifying dryer
	@Time 7200 - 14400 sec	@Time 2.00 - 4.00 hour	

Descriptive Properties	Value	Comments
Color	dark grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China