

Lehmann & Voss LUVOCOM® 20-7847 Polyphthalamide, with carbon fiber and PTFE

Category : Polymer , Thermoplastic , Polyphthalamide (PPA) , Polyphthalamide (PPA), Carbon Fiber + PTFE Filled

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. High-strength and high-stiff parts; low coefficient of expansion. Low influence from moisture and temperature to measures and electrical properties, compared with PA66. Suitable for metal inserts. Improved friction and wear behaviour. Emergency running property. Bearings, sleeves, sliding elements, control disks, gear wheels, duty parts in switches. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-20-7847-Polyphthalamide-with-carbon-fiber-and-PTFE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.32 g/cc	1.32 g/cc	ISO 1183
Water Absorption	<= 0.30 %	<= 0.30 %	23Â°C/24h
Linear Mold Shrinkage	0.00050 - 0.0030 cm/cm	0.00050 - 0.0030 in/in	
Melt Flow	7.0 g/10 min @Load 2.16 kg, Temperature 340 Â°C	7.0 g/10 min @Load 4.76 lb, Temperature 644 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Stress	300 MPa	43500 psi	
Elongation at Yield	2.0 %	2.0 %	
	2.5 %	2.5 %	flexural
Modulus of Elasticity	23.0 GPa	3340 ksi	
Flexural Strength	430 MPa	62400 psi	
Flexural Modulus	20.0 GPa	2900 ksi	
Charpy Impact Unnotched	6.00 J/cmÂ²	28.6 ft-lb/inÂ²	edgewise; ISO 179 1eU
Charpy Impact, Notched	0.800 J/cmÂ²	3.81 ft-lb/inÂ²	ISO 179 1eA

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	165 Â°C	329 Â°F	
	195 Â°C	383 Â°F	short term

Electrical Properties	Metric	English	Comments
Insulation Resistance	<= 1000 ohm	<= 1000 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	330 Â°C	626 Â°F	mass temp
Nozzle Temperature	320 - 330 Â°C	608 - 626 Â°F	
Zone 1	320 - 340 Â°C	608 - 644 Â°F	
Zone 2	320 - 345 Â°C	608 - 653 Â°F	
Zone 3	325 - 350 Â°C	617 - 662 Â°F	
Mold Temperature	135 - 160 Â°C	275 - 320 Â°F	
Drying Temperature	80.0 Â°C @Time 57600 sec	176 Â°F @Time 16.0 hour	Dehumidifying dryer
	105 Â°C @Time 14400 - 18000 sec	221 Â°F @Time 4.00 - 5.00 hour	Vacuum Dryer

Descriptive Properties	Value	Comments
Color	natural color (black)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China