

Lehmann & Voss LUVOCOM® 21-8113 Polyamide 6/6T, with carbon fiber, lubricant modified

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Carbon Fiber Filled

Material Notes:

Applications: Automotive industry, textile- and office machinery, apparatus- and precision engineering. Strong, stiff parts. Dynamic stressed parts at high movement velocity. Improved friction and wear behaviour. Emergency running property. Bearings, sleeves, control disks, gear wheels, pump impellers, gear parts. Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-21-8113-Polyamide-66T-with-carbon-fiber-lubricant-modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	ISO 1183
Water Absorption	<= 0.30 %	<= 0.30 %	23Â°C/24h
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	120 MPa	17400 psi	
Elongation at Yield	1.1 %	1.1 %	
	1.4 %	1.4 %	flexural
Modulus of Elasticity	13.0 GPa	1890 ksi	
Flexural Strength	180 MPa	26100 psi	
Flexural Modulus	11.0 GPa	1600 ksi	
Charpy Impact Unnotched	1.70 J/cmÂ²	8.09 ft-lb/inÂ²	edgewise; ISO 179 1eU

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	135 Â°C	275 Â°F	
	160 Â°C	320 Â°F	short term

Electrical Properties	Metric	English	Comments
Surface Resistance	<= 1.00e+9 ohm	<= 1.00e+9 ohm	
Insulation Resistance	<= 1.00e+9 ohm	<= 1.00e+9 ohm	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	Metric	English	Comments
Nozzle Temperature	330 - 340 Â°C	626 - 644 Â°F	
Zone 1	300 - 340 Â°C	572 - 644 Â°F	
Zone 2	310 - 340 Â°C	590 - 644 Â°F	
Zone 3	320 - 340 Â°C	608 - 644 Â°F	
Mold Temperature	90.0 - 120 Â°C	194 - 248 Â°F	
Drying Temperature	80.0 Â°C @Time 21600 - 57600 sec	176 Â°F @Time 6.00 - 16.0 hour	Dehumidifying dryer
	110 Â°C @Time 14400 - 21600 sec	230 Â°F @Time 4.00 - 6.00 hour	or

Descriptive Properties	Value	Comments
Color	dark grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China