

Lehmann & Voss LUVOCOM[®] PEEK CLASSIX 7994 PEEK, unreinforced

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Unreinforced

Material Notes:

Applications: medical engineeringEspecially suitable for medical parts, superheated steam sterilizable, hydrolysis resistanceHigh chemical resistance parts, non flammable.Inherent flame resistance.Suitable for biocompatible application.Information provided by Lehmann & Voss & Co.KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lehmann-Voss-LUVOCOM-PEEK-CLASSIX-7994-PEEK-unreinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.42 g/cc	1.42 g/cc	ISO 1183
Water Absorption	<= 0.50 %	<= 0.50 %	23Â°C/24h
Linear Mold Shrinkage	0.010 - 0.016 cm/cm	0.010 - 0.016 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Stress	95.0 MPa	13800 psi	
Elongation at Yield	4.0 %	4.0 %	
	6.0 %	6.0 %	flexural
Modulus of Elasticity	4.50 GPa	653 ksi	
Flexural Strength	145 MPa	21000 psi	
Flexural Modulus	4.00 GPa	580 ksi	
Charpy Impact, Notched	0.500 J/cmÂ²	2.38 ft-lb/inÂ²	ISO 179 1eA

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	250 Â°C	482 Â°F	
	260 Â°C	500 Â°F	short term
Deflection Temperature at 1.8 MPa (264 psi)	150 Â°C	302 Â°F	

Electrical Properties	Metric	English	Comments
Surface Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	
Insulation Resistance	>= 1.00e+12 ohm	>= 1.00e+12 ohm	

Processing Properties	Metric	English	Comments
Processing Temperature	390 Â°C	734 Â°F	mass temp
Nozzle Temperature	360 - 380 Â°C	680 - 716 Â°F	
Zone 1	360 - 370 Â°C	680 - 698 Â°F	
Zone 2	380 - 390 Â°C	716 - 734 Â°F	
Zone 3	390 - 400 Â°C	734 - 752 Â°F	
Mold Temperature	170 - 190 Â°C	338 - 374 Â°F	
Drying Temperature	120 Â°C	248 Â°F	or
	@Time 21600 - 28800 sec	@Time 6.00 - 8.00 hour	
	150 Â°C	302 Â°F	Dehumidifying dryer
	@Time 10800 - 21600 sec	@Time 3.00 - 6.00 hour	

Descriptive Properties	Value	Comments
Color	beige red	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China