

Loctite® 5182 Flexible Cure Anaerobic Sealant

Category : Polymer , Adhesive , Thermoset

Material Notes:

Anaerobic Gasketing Loctite® 5182 Flexible Cure Anaerobic Sealant Recommended Primer: 7649 (N). Typical Use: Robotic application on flanges, seals, covers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Loctite-5182-Flexible-CureAnaerobic-Sealant.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	
Viscosity	140000 - 580000 cP	140000 - 580000 cP	Thixotropic

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	149 °C	300 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	30.0 - 1440 min	0.500 - 24.0 hour	Full Cure
	240 - 1440 min	4.00 - 24.0 hour	Full Cure, Unprimed

Descriptive Properties	Value	Comments
Color	Red	
Gap Fill	0.010 in.	Unprimed
	0.02 in.	Primed

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China