

## **Loctite® Durabond® E-40FL Epoxy Adhesive**

Category: Polymer, Adhesive, Thermoset, Epoxy, Epoxy Adhesive

## **Material Notes:**

Epoxy AdhesivesLoctite offers a complete line of one-part and two-part epoxy and urethane adhesives for structural bonding, potting and encapsulating. The Loctite® Durabond® line contains 14 application-specific products designed to outperform the competition in all aspects: better adhesion, better flow, less odor, improved clarity, higher strength, and greater durability. All two-part Durabond® Structural Adhesives are packaged in easy-to-use, side-by-side cartridges for use with our manual dispensers and mix nozzles.Loctite® E-40FL Toughened, flexible, impact resistant Durabond® Epoxy AdhesiveA toughened epoxy with a 40 minute worklife. Grey, flexible, impact resistant.Mix Ratio by Volume, Resin:Hardener = 1:1 Bonding Type: Epoxy

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Loctite-Durabond-E-40FL-Epoxy-Adhesive.php

Physical Properties	Metric	English	Comments
Viscosity	75000 cP	75000 cP	Mixed - medium; Resin - 75,000 cP; Hardener - 65,500 cP

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	75	75	
Adhesive Bond Strength	6.89 - 20.7 MPa	1000 - 3000 psi	Varies with substrates
Peel Strength	0.877 - 7.01 kN/m	5.00 - 40.0 pli	Varies with substrates.

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	30.0 °C	86.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	15.7 kV/mm	400 kV/in	Test run on 1/8" specimens.

Processing Properties	Metric	English	Comments
Pot Life	40 min	40 min	

Descriptive Properties	Value	Comments
Color	Grey	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com



Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China