

Lord Adhesives 8300 Medium Setting, Medium Viscosity Ethyl Cyanoacrylate Adhesive

Category : Polymer , Adhesive , Thermoset , Acrylic/Cyanoacrylate Adhesive

Material Notes:

Lord Cyanoacrylate Adhesives Lord® Cyanoacrylate Adhesives were developed for production situations requiring instant bonds and immediate handling strength, particularly when bonding rubber, metals and plastics. Lord Cyanoacrylate Adhesives offer these benefits:

Instant Cure. Lord Cyanoacrylate Adhesives develop strong bonds with setting times ranging from 5 to 130 seconds. **Ease of Use.** Lord Cyanoacrylate Adhesives are one-component systems that facilitate set-up and minimize production costs. **Good Environmental Resistance.** Lord Cyanoacrylate Adhesives offer excellent resistance to weathering and aging. Lord Adhesives 8300 Medium Setting, Medium Viscosity Ethyl Cyanoacrylate Adhesive Medium setting. Medium viscosity. For bonding O-rings and elastomeric materials. Suitable for bonding more difficult substrates such as EPDM and Viton. Especially helpful for bonding loudspeaker isolator rings. Will qualify for USP Class VI approval. MIL-A-46050C Type II, Class 1 Approved.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lord-Adhesives-8300-Medium-Setting-Medium-Viscosity-Ethyl-Cyanoacrylate-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	
Viscosity	20 cP	20 cP	

Processing Properties	Metric	English	Comments
Cure Time	0.0167 - 0.0333 min	0.000278 - 0.000556 hour	Rubber set time
	0.0333 - 0.0500 min	0.000556 - 0.000833 hour	Plastic set time

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China