

Lord Adhesives 9010 Medium Viscosity, Odorless, Non-Frosting Methoxyethyl Cyanoacrylate Adhesive

Category : Polymer , Adhesive , Thermoset , Acrylic/Cyanoacrylate Adhesive

Material Notes:

Lord Cyanoacrylate Adhesives Lord® Cyanoacrylate Adhesives were developed for production situations requiring instant bonds and immediate handling strength, particularly when bonding rubber, metals and plastics. Lord Cyanoacrylate Adhesives offer these benefits:

Instant Cure. Lord Cyanoacrylate Adhesives develop strong bonds with setting times ranging from 5 to 130 seconds. **Ease of Use.** Lord Cyanoacrylate Adhesives are one-component systems that facilitate set-up and minimize production costs. **Good Environmental Resistance.** Lord Cyanoacrylate Adhesives offer excellent resistance to weathering and aging. Lord Adhesives 9010 Medium Viscosity, Odorless, Non-Frosting Methoxyethyl Cyanoacrylate Adhesive Medium viscosity. Odorless and non-frosting. General purpose adhesive formulated for cosmetically critical applications because it will not etch thermoplastic surfaces. Odorless feature eliminates need for special ventilation. Will qualify for USP Class VI approval.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lord-Adhesives-9010-Medium-Viscosity-Odorless-Non-Frosting-Methoxyethyl-Cyanoacrylate-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0386 lb/in ³	
Viscosity	150 cP	150 cP	

Processing Properties	Metric	English	Comments
Cure Time	0.0833 - 0.333 min	0.00139 - 0.00556 hour	Plastic set time
	0.0833 - 0.333 min	0.00139 - 0.00556 hour	Rubber set time
	0.417 - 0.667 min	0.00694 - 0.0111 hour	Metal set time

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China