

## Lubrizol Advanced Materials Pearlthane® MB-9010 Thermoplastic Polyurethane Elastomer

Category : Ceramic , Oxide , Titanium Oxide , Polymer , Thermoplastic , Polyurethane, TP

### Material Notes:

Pearlthane® MB-9010 is a TPU-based color masterbatch, supplied in the form of homogenously white-colored pellets. It is specially intended for coloring TPUs (either polyester or polyether-based), for extrusion, injection molding or calendaring processes. Applications: Pearlthane MB-9010 can be mixed with any items of Merquinsa's Pearlthane or Pearlcoat lines (either polyester or polyether-based) intended for applications obtained by extrusion, injection molding or calendaring. A 2% usage level (on TPU, by weight) is recommended. Higher levels can be considered, depending on the requirements of the end-product. A good color consistency requires an accurate dosing and good distribution in the TPU.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-Advanced-Materials-Pearlthane-MB-9010-Thermoplastic-Polyurethane-Elastomer.php](http://www.lookpolymers.com/polymer_Lubrizol-Advanced-Materials-Pearlthane-MB-9010-Thermoplastic-Polyurethane-Elastomer.php)

Physical Properties	Metric	English	Comments
Apparent Bulk Density	1.05 g/cc	0.0379 lb/in <sup>3</sup>	ASTM D-1875

Component Elements Properties	Metric	English	Comments
TiO <sub>2</sub>	60 %	60 %	

Processing Properties	Metric	English	Comments
Processing Temperature	<= 240 Â°C	<= 464 Â°F	
Drying Temperature	100 - 110 Â°C @Time 3600 - 7200 sec	212 - 230 Â°F @Time 1.00 - 2.00 hour	In hot air circulatory, vacuum, or desiccant-air dryer

Descriptive Properties	Value	Comments
Colour Index n0	RAL 9010	
Lightfastness	8	(1-8) Scale of blue tones; DIN 53 389

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China