

## Lubrizol ESTANE® 58630 Ether Based Thermoplastic Polyurethane (European Grade)

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Ether Grade

### Material Notes:

**Description:** Estane® thermoplastic polyurethanes (TPUs) include elastomeric materials that bridge the gap between flexible rubber and rigid plastics. These materials offer toughness and durability in a flexible thermoplastic elastomer system that is easy to process in a wide range of equipment. The Estane® TPU portfolio of products offers high performance polyester - and polyether - based resins and compounds in a broad range of hardnesses to meet a variety of application needs. **Benefits of Estane® TPU:** Outstanding Abrasion and Wear Resistance, Excellent Low Temperature Flexibility, Superior Toughness and Durability, Ease of Processing and Manufacturing, Flexibility, Colorability and Paintability with no adhesion promoter. **Applications:** Film & Sheet, Fabric coating & melt coating, Wire & Cable, Hose, Tube & Profile, Custom molding, Custom compounding. **Automotive interior/chassis and exterior painted trim.** **Specific Notes for this Material:** Low blocking and low temperature flexibility. Information provided by Noveon, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-ESTANE-58630-Ether-Based-Thermoplastic-Polyurethane-European-Grade.php](http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-58630-Ether-Based-Thermoplastic-Polyurethane-European-Grade.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.11 g/cc	1.11 g/cc	DIN 53479

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	82	82	DIN 53505
Tensile Strength, Ultimate	31.0 MPa	4500 psi	DIN 53504
Elongation at Break	700 %	700 %	DIN 53504
50% Modulus	0.00400 GPa	0.580 ksi	DIN 53504
100% Modulus	0.00490 GPa	0.711 ksi	DIN 53504
300% Modulus	0.00690 GPa	1.00 ksi	DIN 53504
Tear Strength	46.0 kN/m	262 pli	DIN 53515
Abrasion	35	35	mm<sup>3</sup>; DIN 53516
Compression Set	25 %	25 %	70 hrs./22°C; DIN 53517
	70 %	70 %	24 hrs./70°C; DIN 53517

Thermal Properties	Metric	English	Comments
Vicat Softening Point	63.0 °C	145 °F	A50; DIN 53460
Brittleness Temperature	-70.0 °C	-94.0 °F	DIN 53546

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China