

## Lubrizol ESTANE® T4057 Ether Based Thermoplastic Polyurethane (European Grade)

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Ether Grade

### Material Notes:

**Description:** Estane® thermoplastic polyurethanes (TPUs) include elastomeric materials that bridge the gap between flexible rubber and rigid plastics. These materials offer toughness and durability in a flexible thermoplastic elastomer system that is easy to process in a wide range of equipment. The Estane® TPU portfolio of products offers high performance polyester - and polyether - based resins and compounds in a broad range of hardnesses to meet a variety of application needs. **Benefits of Estane® TPU:** Outstanding Abrasion and Wear ResistanceExcellent Low Temperature FlexibilitySuperior Toughness and DurabilityEase of Processing and Manufacturing FlexibilityColorability and Paintability with no adhesion promoter**Applications:** Film & SheetFabric coating & melt coatingWire & CableHose, Tube & ProfileCustom moldingCustom compoundingAutomotive interior/chassis and exterior painted trim**Specific Notes for this Material:** Conductive Information provided by Noveon, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-ESTANE-T4057-Ether-Based-Thermoplastic-Polyurethane-European-Grade.php](http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-T4057-Ether-Based-Thermoplastic-Polyurethane-European-Grade.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.17 g/cc	1.17 g/cc	DIN 53479

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	94	94	DIN 53505
Hardness, Shore D	40	40	DIN 53505
Tensile Strength, Ultimate	8.70 MPa	1260 psi	DIN 53504
Elongation at Break	480 %	480 %	DIN 53504
50% Modulus	0.00790 GPa	1.15 ksi	DIN 53504
100% Modulus	0.00860 GPa	1.25 ksi	DIN 53504
300% Modulus	0.00940 GPa	1.36 ksi	DIN 53504
Tear Strength	60.0 kN/m	342 pli	DIN 53515
Abrasion	65	65	mg/1000 rot; DIN 53516
Compression Set	38 %	38 %	24 hrs./70°C; DIN 53517
	55 %	55 %	70 hrs./22°C; DIN 53517

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China