

## **Lubrizol ESTANE® T5191 Ether Based Thermoplastic Polyurethane (European Grade)**

Category: Polymer, Thermoplastic, Elastomer, TPE, Polyurethane, TP, Thermoplastic Polyurethane, Elastomer, Ether Grade

## **Material Notes:**

Description: Estane® thermoplastic polyurethanes (TPUs) include elastomeric materials that bridge the gap between flexible rubber and rigid plastics. These materials offer toughness and durability in a flexible thermoplastic elastomer system that is easy to process in a wide range of equipment. The Estane® TPU portfolio of products offers high performance polyester - and polyether - based resins and compounds in a broad range of hardnesses to meet a variety of application needs.Benefits of Estane® TPU: Outstanding Abrasion and Wear ResistanceExcellent Low Temperature FlexibilitySuperior Toughness and DurabilityEase of Processing and Manufacturing FlexibilityColorability and Paintability with no adhesion promoterApplications: Film & SheetFabric coating & melt coatingWire & CableHose, Tube & ProfileCustom moldingCustom compoundingAutomotive interior/chassis and exterior painted trimSpecific Notes for this Material: Electrostatic decay Information provided by Noveon, Inc.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Lubrizol-ESTANE-T5191-Ether-Based-Thermoplastic-Polyurethane-European-Grade.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.23 g/cc	1.23 g/cc	DIN 53479

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90	90	DIN 53505
Tensile Strength, Ultimate	38.0 MPa	5510 psi	DIN 53504
Elongation at Break	630 %	630 %	DIN 53504
50% Modulus	0.00590 GPa	0.856 ksi	DIN 53504
100% Modulus	0.00700 GPa	1.02 ksi	DIN 53504
300% Modulus	0.0123 GPa	1.78 ksi	DIN 53504
Tear Strength	70.0 kN/m	399 pli	DIN 53515
Abrasion	38	38	mm <sup>3</sup> ; DIN 53516
Compression Set	25 %	25 %	24 hrs./70°C; DIN 53517
	68 %	68 %	70 hrs./22°C; DIN 53517

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-70.0 °C	-94.0 °F	DIN 53546

## Contact Songhan Plastic Technology Co.,Ltd.



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China