

Lubrizol ESTANE® X1013 Ether Based Thermoplastic Polyurethane (European Grade)

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Ether Grade

Material Notes:

Description: Estane® thermoplastic polyurethanes (TPUs) include elastomeric materials that bridge the gap between flexible rubber and rigid plastics. These materials offer toughness and durability in a flexible thermoplastic elastomer system that is easy to process in a wide range of equipment. The Estane® TPU portfolio of products offers high performance polyester - and polyether - based resins and compounds in a broad range of hardnesses to meet a variety of application needs. Benefits of Estane® TPU: Outstanding Abrasion and Wear Resistance Excellent Low Temperature Flexibility Superior Toughness and Durability Ease of Processing and Manufacturing Flexibility Colorability and Paintability with no adhesion promoter Applications: Film & Sheet Fabric coating & melt coating Wire & Cable Hose, Tube & Profile Custom molding Custom compounding Automotive interior/chassis and exterior painted trim Information provided by Noveon, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-X1013-Ether-Based-Thermoplastic-Polyurethane-European-Grade.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	DIN 53479

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	70	70	DIN 53505
Tensile Strength, Ultimate	42.0 MPa	6090 psi	DIN 53504
Elongation at Break	355 %	355 %	DIN 53504
50% Modulus	0.0204 GPa	2.96 ksi	DIN 53504
100% Modulus	0.0213 GPa	3.09 ksi	DIN 53504
300% Modulus	0.0358 GPa	5.19 ksi	DIN 53504
Flexural Stiffness	430.00 MPa	62366 psi	ASTM D747
Tear Strength	175 kN/m	999 pli	DIN 53515
Abrasion	81	81	mm ³ ; DIN 53516

Thermal Properties	Metric	English	Comments
Vicat Softening Point	99.0 °C	210 °F	A50; DIN 53460

Descriptive Properties	Value	Comments
E-Modulus	420 mm/min	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China