

Lubrizol Isoplast® 101LGF40BLK Engineering Thermoplastic Polyurethane Resin

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Glass Fiber Reinforced

Material Notes:

Available in Americas, Europe, Middle East, Africa, India and Asia
Data provided by Lubrizol
Lubrizol acquired the Isoplast product line from Dow in 2009.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-Isoplast-101LGF40BLK-Engineering-Thermoplastic-Polyurethane-Resin.php

Physical Properties	Metric	English	Comments
Density	1.51 g/cc	0.0546 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	186 MPa	27000 psi	ASTM D638
Tensile Strength, Yield	186 MPa	27000 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Elongation at Yield	2.0 %	2.0 %	ASTM D638
Tensile Modulus	10.0 GPa	1450 ksi	ASTM D638
Flexural Strength	248 MPa	36000 psi	ASTM D790
Flexural Modulus	9.60 GPa	1390 ksi	ASTM D790
Izod Impact, Unnotched	3.20 J/cm	5.99 ft-lb/in	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 °C	@Thickness 0.126 in, Temperature 73.4 °F	
	3.20 J/cm	5.99 ft-lb/in	ASTM D256
	@Thickness 3.20 mm, Temperature -40.0 °C	@Thickness 0.126 in, Temperature -40.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	14.0 µm/m-°C	7.78 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 1.8 MPa (264 psi)	93.0 °C	199 °F	Annealed; ASTM D648
	93.0 °C	199 °F	Unannealed; ASTM D648

Thermal Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Melt Temperature	240 - 260 °C	464 - 500 °F	
Mold Temperature	65.0 - 90.0 °C	149 - 194 °F	
Drying Temperature	80.0 - 100 °C	176 - 212 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China