

Lucas-Milhaupt Silvaloy® 0 Brazing Alloy

Category : Metal , Nonferrous Metal , Copper Alloy , Solder/Braze Alloy

Material Notes:

Silvaloy 0 is used for the brazing of copper and copper alloys, brass and bronze. It can also be used on silver, tungsten and molybdenum. It is primarily used for the joining of copper-to-copper on vibration free joints. It is very effective for joining tight fittings and tubing. Silvaloy 0 is extremely fluid at brazing temperatures and will penetrate joints with very little clearance. Applications: The phosphorus content of Silvaloy 0 acts as a fluxing agent and no flux is necessary when brazing copper to copper joints. However, when used with a copper alloy or one of the other brazeable metals, a flux must be used to promote wetting, bonding, and flow throughout the joint. The flow point of Silvaloy 0 is 1350°F. Information provided by Lucas-Milhaupt Warwick, LLC (formerly Wolverine Joining Technologies).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucas-Milhaupt-Silvaloy-0-Brazing-Alloy.php

Physical Properties	Metric	English	Comments
Specific Gravity	8.00 g/cc	8.00 g/cc	
Density	8.00 g/cc	0.289 lb/in ³	

Thermal Properties	Metric	English	Comments
Melting Point	710 - 793 °C	1310 - 1460 °F	
Solidus	710 °C	1310 °F	
Liquidus	793 °C	1460 °F	
Maximum Service Temperature, Air	149 °C	300 °F	continuous
	204 °C	400 °F	intermittent

Component Elements Properties	Metric	English	Comments
Copper, Cu	92.35 - 93 %	92.35 - 93 %	As balance
Other, total	<= 0.15 %	<= 0.15 %	
Phosphorous, P	7.0 - 7.5 %	7.0 - 7.5 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000232 ohm-cm	0.0000232 ohm-cm	

Processing Properties	Metric	English	Comments
Processing Temperature	732 - 843 °C	1350 - 1550 °F	Brazing Temperature

Descriptive Properties	Value	Comments
Color	Copper Yellow	
Electrical Conductivity (% IACS)	7.5	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China