

## Lucas-Milhaupt Silvaloy® A38T Brazing Alloy

Category : Metal , Nonferrous Metal , Precious Metal , Silver Alloy , Solder/Braze Alloy

### Material Notes:

Silvaloy A38T is used for joining ferrous metals, copper, copper alloys, nickel, nickel alloys and combinations of these metals. The tin content provides good wetting on many difficult to wet metals such as stainless steel and tungsten carbide. This alloy, being free of Pb or Cd is preferred for long heating cycles and is suitable for use in controlled atmosphere brazing without flux. The largest use of this alloys is the furnace brazing although it is also suitable for other brazing procedures. Information provided by Lucas-Milhaupt Warwick, LLC (formerly Wolverine Joining Technologies).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lucas-Milhaupt-Silvaloy-A38T-Brazing-Alloy.php](http://www.lookpolymers.com/polymer_Lucas-Milhaupt-Silvaloy-A38T-Brazing-Alloy.php)

Physical Properties	Metric	English	Comments
Specific Gravity	9.05 g/cc	9.05 g/cc	
Density	9.05 g/cc	0.327 lb/in <sup>3</sup>	

Thermal Properties	Metric	English	Comments
Melting Point	649 - 721 °C	1200 - 1330 °F	
Solidus	649 °C	1200 °F	
Liquidus	721 °C	1330 °F	
Maximum Service Temperature, Air	204 °C	400 °F	continuous
	316 °C	600 °F	intermittent

Component Elements Properties	Metric	English	Comments
Copper, Cu	31 - 33 %	31 - 33 %	
Other, total	<= 0.15 %	<= 0.15 %	
Silver, Ag	37 - 39 %	37 - 39 %	
Tin, Sn	1.5 - 2.5 %	1.5 - 2.5 %	
Zinc, Zn	26 - 30 %	26 - 30 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000950 ohm-cm	0.00000950 ohm-cm	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Temperature Processing Properties	721 - 843 Å°C Metric	1330 - 1550 Å°F English	Brazing Temperature Comments
Descriptive Properties		Value	Comments
Color		Pale Yellow	
Electrical Conductivity (% IACS)		18	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China