

## Lucent Polymers GPB-130 Polybutylene Terephthalate, 30% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled

### Material Notes:

Add "R" for Added ReleaseAdd "U" for UV StabilizerInformation provided by Lucent Polymers, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lucent-Polymers-GPB-130-Polybutylene-Terephthalate-30-Glass-Fiber-Reinforced.php](http://www.lookpolymers.com/polymer_Lucent-Polymers-GPB-130-Polybutylene-Terephthalate-30-Glass-Fiber-Reinforced.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	1/8" Section

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	124.14 MPa	18005 psi	ASTM D638
Elongation at Break	>= 3.0 %	>= 3.0 %	ASTM D638
Flexural Strength	172.41 MPa	25006 psi	ASTM D790
Flexural Modulus	6.483 GPa	940.2 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Thickness 3.17 mm, Temperature 22.8 Å°C	1.50 ft-lb/in @Thickness 0.125 in, Temperature 73.0 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	157.22 Å°C	315.00 Å°F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China