

Lucite International Colacryl Â® B866 Acrylic Dental Resin

Category : Polymer , Thermoplastic , Acrylic (PMMA)

Material Notes:

Cold-curing denture repair resin with Methyl Methacrylate based homopolymers. Features fast polymerisation, easy mixing, good clarity, short hydroflask cure cycles, and excellent pigment acceptance. Information provided by Lucite International

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucite-International-Colacryl-B866-Acrylic-Dental-Resin.php

Physical Properties	Metric	English	Comments
Particle Size	30 - 46 Âµm	30 - 46 Âµm	
Molecular Weight	300000 - 900000 g/mol	300000 - 900000 g/mol	

Processing Properties	Metric	English	Comments
Cure Time	20.0 min @Pressure 0.207 MPa, Temperature 40.0 Â°C	0.333 hour @Pressure 30.0 psi, Temperature 104 Â°F	

Descriptive Properties	Value	Comments
Residual peroxide (%)	2.5 - 3.1	
Set Time (min)	35	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China