

## Lucite International Diakon® CMG314V Acrylic Polymer

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded

### Material Notes:

Information provided by Lucite International

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lucite-International-Diakon-CMG314V-Acrylic-Polymer.php](http://www.lookpolymers.com/polymer_Lucite-International-Diakon-CMG314V-Acrylic-Polymer.php)

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.30 %	0.30 %	ISO 62
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	
Melt Flow	3.0 g/10 min	3.0 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	98	98	ISO 2039-2
Ball Indentation Hardness	185 MPa	26800 psi	ISO 2039-1
Tensile Strength	83.0 MPa	12000 psi	ISO 527
Elongation at Break	5.0 %	5.0 %	ISO 527
Flexural Strength	115 MPa	16700 psi	ISO 178
Flexural Modulus	3.20 GPa	464 ksi	ISO 178
Izod Impact, Notched (ISO)	2.00 kJ/m <sup>2</sup>	0.952 ft-lb/in <sup>2</sup>	ISO 180/1A
Charpy Impact, Notched	0.200 J/cm <sup>2</sup>	0.952 ft-lb/in <sup>2</sup>	ISO 179/1eA
	2.00 J/cm <sup>2</sup>	9.52 ft-lb/in <sup>2</sup>	ISO 179/1eU

Thermal Properties	Metric	English	Comments
CTE, linear	71.0 Åµm/m-Å°C	39.4 Åµin/in-Å°F	ASTM E831
Vicat Softening Point	108 Å°C	226 Å°F	ISO 306B
	117 Å°C	243 Å°F	ISO 306A
Heat Distortion Temperature	102 Å°C	216 Å°F	ISO 75A
	105 Å°C	221 Å°F	ISO 75B
Flammability, UL94	HB	HB	

Thermal Properties	Metric	English	Comments
Optical Properties	Metric	English	Comments
Refractive Index	1.49	1.49	ISO 489
Haze	0.40 %	0.40 %	ASTM D1003
Transmission, Visible	92 %	92 %	ASTM D1003

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China