

Lucite International Diakon® Frost 952 70 Acrylic Polymer

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded

Material Notes:

Information provided by Lucite International

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucite-International-Diakon-Frost-952-70-Acrylic-Polymer.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ISO 1183
Water Absorption	0.30 %	0.30 %	ISO 62
Melt Flow	1.5 g/10 min	1.5 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	90	90	ISO 2039-2
Ball Indentation Hardness	170 MPa	24700 psi	ISO 2039-1 (H 961-30)
Tensile Strength	72.0 MPa	10400 psi	ISO 527
Elongation at Break	6.4 %	6.4 %	ISO 527
Flexural Strength	120 MPa	17400 psi	ISO 178
Flexural Modulus	3.20 GPa	464 ksi	ISO 178
Izod Impact, Notched (ISO)	1.60 kJ/m ²	0.761 ft-lb/in ²	ISO 180/1A
Charpy Impact Unnotched	2.20 J/cm ²	10.5 ft-lb/in ²	ISO 179/1eU
Charpy Impact, Notched	0.200 J/cm ²	0.952 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	99.0 °C	210 °F	ISO 75B
Deflection Temperature at 1.8 MPa (264 psi)	95.0 °C	203 °F	ISO 75A
Vicat Softening Point	101 °C	214 °F	ISO 306B
	108 °C	226 °F	ISO 306A
Flammability, UL94	HB	HB	
Glow Wire Test	650 °C	1200 °F	IEC 695-2-1

Optical Properties	Metric	English	Comments
Haze	97.5 %	97.5 %	ASTM D1003
Transmission, Visible	80.5 %	80.5 %	ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China