

## Lucky IH-830 Acrylic, Injection Grade

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded

**Material Notes:**

Similar to grade EH-910, but with higher flow for injection molding. May be UV stabilized. General Lucky PMMA qualities:

Transparent/elegant appearance, high heat and weather resistance, excellent chemical resistance and coloring capability.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lucky-IH-830-Acrylic-Injection-Grade.php](http://www.lookpolymers.com/polymer_Lucky-IH-830-Acrylic-Injection-Grade.php)

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	ASTM D955-51
Melt Flow	2.3 g/10 min	2.3 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	97	97	ASTM D785
Tensile Strength, Ultimate	74.0 MPa	10700 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Yield Strength	133 MPa	19300 psi	ASTM D790
Flexural Modulus	3.30 GPa	479 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	98.0 Â°C	208 Â°F	Heat Distortion Temp
	98.0 Â°C	208 Â°F	Deflection Temp; Load not reported; ASTM D648
Vicat Softening Point	105 Â°C	221 Â°F	ASTM D1525
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 3.17 mm	@Thickness 0.125 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.49	1.49	ASTM D542
Transmission, Visible	92 %	92 %	ASTM D1003

Electrical Properties	Metric	English	Comments
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China