Lucobit Lucobit® 1210 Ethylene Copolymer Bitumen

Category : Polymer , Thermoplastic , Polyolefin

Material Notes:

Lucobit® combines the positive properties of polyolefins and bitumen. The material is black and consists of mixtures based on high quality polyethylene copolymers with varying additions of special and amorphous bitumen. Bitumen is integrated homogeneously in the polymer matrix and thus can be processed as free-flowing granules on conventional processing equipment.Lucobit® has proven to be a robust and reliable raw material for roofing and sealing membranes. Product provides improvements in:• corrosion protection • thermal insulation• weathering resistance • thermal stability• bonding and weldability • anti-static effect• filler acceptance • shrinkage reduction• environmental stress crack resistanceInformation provided by Lucobit AG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucobit-Lucobit-1210-Ethylene-Copolymer-Bitumen.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------------------------------------|--------------------------------------|----------|
| Density | 0.970 g/cc | 0.0350 lb/in³ | ISO 1183 |
| | >= 25 g/10 min | >= 25 g/10 min | |
| Melt Flow | @Load 2.16 kg, Temperature 190 °C | @Load 4.76 lb, Temperature 374 °F | ISO 1133 |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|------------|----------|----------|
| Hardness, Shore A | 76 | 76 | ISO 868 |
| Modulus of Elasticity | 0.0170 GPa | 2.47 ksi | ISO 527 |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------|----------|---|
| Minimum Service Temperature, Air | -20.0 °C | -4.00 °F | Low Temperature Flexural Test; DIN 53361 |

| Processing Properties | Metric | English | Comments |
|------------------------|----------------|---------------|-----------|
| Processing Temperature | 150 - 180 °C | 302 - 356 °F | Profiles |
| | 160 - 230 °C | 320 - 446 °F | Membranes |
| | 160 - 240 °C | 320 - 464 °F | Coatings |
| Melt Temperature | 160 - 220 °C | 320 - 428 °F | |
| Mold Temperature | 10.0 - 40.0 °C | 50.0 - 104 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com



Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China