

LyondellBasell Alathon® L5885 High Density Polyethylene

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Film Grade

Material Notes:

ApplicationsALATHON L 5885 is a medium molecular weight high density homopolymer for use in blown film applications. Typical applications include those low WVTR requirements.**Regulatory Status**L 5855 meets the requirements of Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information.

Processing TechniquesSpecific recommendations for processing LB 0100-00 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.**Typical Extrusion Conditions: 2.0 Mil Film; Melt Temperature- 390°-410°F(199°**This product is from the former Equistar product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Alathon-L5885-High-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.958 g/cc	0.0346 lb/in ³	ASTM D792
Thickness	50.8 microns	2.00 mil	
Melt Flow	0.85 g/10 min	0.85 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	25.5 MPa	3700 psi	ASTM D882
Film Tensile Strength at Yield, TD	26.2 MPa	3800 psi	ASTM D882
Film Elongation at Break, MD	700 %	700 %	ASTM D882
Film Elongation at Break, TD	750 %	750 %	ASTM D882
Elmendorf Tear Strength MD	18 g	18 g	ASTM D1922
Elmendorf Tear Strength TD	900 g	900 g	ASTM D1922
1% Secant Modulus, MD	862 MPa	125000 psi	ASTM D882
1% Secant Modulus, TD	1000 MPa	145000 psi	ASTM D822

Processing Properties	Metric	English	Comments
Melt Temperature	199 - 210 °C	390 - 410 °F	Typical Extrusion

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China