

LyondellBasell Alathon® M6030 High Density Polyethylene

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Film Grade

Material Notes:

ApplicationsALATHON M 6030 is a medium molecular weight high density homopolymer with extremely low gel content. Typical applications for this resin are cast film, coextrusion and dry food packaging.**Regulatory Status**M 6030 meets the requirements of Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information. **Processing Techniques**Specific recommendations for processing M 6030 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.**Typical Extrusion Conditions**Melt Temperature- 390°F(199°C)This product is from the former Equistar product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Alathon-M6030-High-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.960 g/cc	0.0347 lb/in ³	ASTM D792
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	22.1 MPa	3200 psi	ASTM D822
Film Tensile Strength at Yield, TD	20.7 MPa	3000 psi	ASTM D822
Film Elongation at Break, MD	860 %	860 %	ASTM D822
Film Elongation at Break, TD	850 %	850 %	ASTM D822
Elmendorf Tear Strength MD	20 g	20 g	ASTM D1922
Elmendorf Tear Strength TD	500 g	500 g	ASTM D1922
1% Secant Modulus, MD	689 MPa	100000 psi	ASTM D822
1% Secant Modulus, TD	827 MPa	120000 psi	ASTM D822

Processing Properties	Metric	English	Comments
Melt Temperature	199 °C	390 °F	Typical Extrusion

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China