

## LyondellBasell Hiclass SB224-3 Polypropylene Copolymer, 30% Glass Fiber

Category : Polymer , Thermoplastic , Polypropylene (PP)

### Material Notes:

**Key Features:** conventional melt flow, medium high modulus, chemically coupled, glass fiber-reinforced polypropylene copolymer, high impact strength, high stiffness, good processability  
**Applications:** wheel well housings, garden equipment housings, recreational vehicle components  
**Description:** Hiclass SB224-3 conventional melt flow, chemically coupled, 30% glass fiber-reinforced polypropylene copolymer has an excellent balance of strength, stiffness and impact resistance. Information provided by Montell Polyolefins. LyondellBasell is the successor company to Montell.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LyondellBasell-Hiclass-SB224-3-Polypropylene-Copolymer-30-Glass-Fiber.php](http://www.lookpolymers.com/polymer_LyondellBasell-Hiclass-SB224-3-Polypropylene-Copolymer-30-Glass-Fiber.php)

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	Tool, Montell
Melt Flow	5.0 g/10 min @Load 2.16 kg, Temperature 230 °C	5.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	66.0 MPa	9570 psi	ASTM D638
Elongation at Break	8.0 %	8.0 %	ASTM D638
Flexural Modulus	3.90 GPa	566 ksi	Tangent at 0.05 in/min; ASTM D790A
Izod Impact, Notched	2.40 J/cm	4.50 ft-lb/in	ASTM D256A
Izod Impact, Unnotched	8.00 J/cm	15.0 ft-lb/in	ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	155 °C	311 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	138 °C	280 °F	ASTM D648
UL RTI, Mechanical with Impact	110 °C @Thickness 1.60 mm	230 °F @Thickness 0.0630 in	
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**