

## LyondellBasell Lupolen® 4261 A HDPE, Blow Molding Grade

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Blow Molding Grade

### Material Notes:

Easy-to-process bow molding grade for technical containers such as fuel tanks, petrol filler inlets, expansion tanks, horticultural spray tanks, tanks for lawnmowers, disposable containers (up to 1000 l), containers for transportation and storage, etc. Data was collected by ISO methods and originally provided by BASF. The Lupolen® product line is now produced by Basell.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LyondellBasell-Lupolen-4261-A-HDPE-Blow-Molding-Grade.php](http://www.lookpolymers.com/polymer_LyondellBasell-Lupolen-4261-A-HDPE-Blow-Molding-Grade.php)

Physical Properties	Metric	English	Comments
Density	0.945 g/cc	0.0341 lb/in <sup>3</sup>	
Water Absorption	0.010 %	0.010 %	
Moisture Absorption at Equilibrium	0.010 %	0.010 %	
High Load Melt Index	0.10 g/10 min	0.10 g/10 min	
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	24.0 MPa	3480 psi	
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	10 %	10 %	
Tensile Modulus	0.850 GPa	123 ksi	
Tensile Impact Strength	260 kJ/m <sup>2</sup>	124 ft-lb/in <sup>2</sup>	
Tensile Creep Modulus, 1 hour	360 MPa	52200 psi	
Tensile Creep Modulus, 1000 hours	250 MPa	36300 psi	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	170 µm/m-°C	94.4 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	130 °C	266 °F	
Deflection Temperature at 0.46 MPa (66 psi)	70.0 °C	158 °F	
Deflection Temperature at 1.8 MPa	42.0 °C	108 °F	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	75.0 Å°C	167 Å°F	
Flammability, UL94	HB @Thickness 0.400 mm	HB @Thickness 0.0157 in	
Oxygen Index	17 %	17 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Constant	2.4 @Frequency 100 Hz	2.4 @Frequency 100 Hz	
	2.4 @Frequency 1e+6 Hz	2.4 @Frequency 1e+6 Hz	
Dielectric Strength	150 kV/mm	3810 kV/in	
Dissipation Factor	0.00020 @Frequency 100 Hz	0.00020 @Frequency 100 Hz	
	0.00020 @Frequency 1e+6 Hz	0.00020 @Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China