

LyondellBasell Lupolen® 5231 HX HDPE, Impact Grade

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Impact Grade

Material Notes:

Medium flow, impact resistant, very stress-crack resistant grade for closures, bottles that contain carbonated liquids, storage and tote boxes, as well as engineering components. Data was collected by ISO methods and originally provided by BASF. The Lupolen® product line is now produced by Basell.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Lupolen-5231-HX-HDPE-Impact-Grade.php

Physical Properties	Metric	English	Comments
Density	0.952 g/cc	0.0344 lb/in ³	
Water Absorption	0.010 %	0.010 %	
Moisture Absorption at Equilibrium	0.10 %	0.10 %	
Linear Mold Shrinkage, Flow	0.023 cm/cm	0.023 in/in	
Linear Mold Shrinkage, Transverse	0.024 cm/cm	0.024 in/in	
Melt Flow	3.3 g/10 min @Load 2.16 kg, Temperature 190 °C	3.3 g/10 min @Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	25.0 MPa	3630 psi	
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	9.0 %	9.0 %	
Tensile Modulus	1.10 GPa	160 ksi	
Tensile Impact Strength	90.0 kJ/m ²	42.8 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	165 µm/m-°C	91.7 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	133 °C	271 °F	
Deflection Temperature at 0.46 MPa (66 psi)	73.0 °C	163 °F	
Deflection Temperature at 1.8 MPa	44.0 °C	111 °F	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	75.0 Å°C	167 Å°F	
Flammability, UL94	HB @Thickness 0.400 mm	HB @Thickness 0.0157 in	
Oxygen Index	17 %	17 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Constant	2.4 @Frequency 100 Hz	2.4 @Frequency 100 Hz	
	2.4 @Frequency 1e+6 Hz	2.4 @Frequency 1e+6 Hz	
Dielectric Strength	150 kV/mm	3810 kV/in	
Dissipation Factor	0.00020 @Frequency 100 Hz	0.00020 @Frequency 100 Hz	
	0.00020 @Frequency 1e+6 Hz	0.00020 @Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China