

LyondellBasell Petrothene® NA345013 Low Density Polyethylene (Film Extrusion)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

Material Notes:

Applications PETROTHENE NA 345 is a series of homopolymer resins combining premium clarity with strength and stiffness. In addition, NA 345 exhibits good impact strength on both flat and creased film. NA 345 is recommended for textile packaging, light produce, bread bags and other thin packaging films enhanced by clarity and sparkle. The optimal values of NA 345 actually improve with decrease in film gauge and are maintained at a wide die gap settings. This fact leads to important cost savings. Film can be drawn down to a minimum gauge consistent with required physical properties, with the assurance that optical properties will not suffer, but improve. With wider die gaps back pressures are reduced, as are extrusion costs. Regulatory Status NA 345 meets the requirements of the Food and Drug Administration regulation 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "articles or components of articles intended for use in contact with food." Specific limitations or conditions. This product is from the former Equistar product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Petrothene-NA345013-Low-Density-Polyethylene-Film-Extrusion.php

Physical Properties	Metric	English	Comments
Density	0.921 g/cc	0.0333 lb/in ³	ASTM D1505
Thickness	31.8 microns	1.25 mil	2:1 BUR; 25 mil die gap
Melt Flow	1.8 g/10 min	1.8 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, TD	11.0 MPa	1600 psi	ASTM D882
Film Elongation at Break, MD	300 %	300 %	ASTM D882
Film Elongation at Break, TD	500 %	500 %	ASTM D882
Elmendorf Tear Strength MD	360 g	360 g	ASTM D1922
Elmendorf Tear Strength TD	200 g	200 g	ASTM D1922
Dart Drop Test	90.0 g	0.198 lb	F ₅₀ ; ASTM D1709
Film Tensile Strength at Break, MD	27.6 MPa	4000 psi	ASTM D882
Film Tensile Strength at Break, TD	23.4 MPa	3400 psi	ASTM D882
1% Secant Modulus, MD	179 MPa	26000 psi	ASTM D882
1% Secant Modulus, TD	207 MPa	30000 psi	ASTM D882

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Vicat Softening Point Thermal Properties	100 Å°C Metric	212 Å°F English	ASTM D1525 Comments
---	-------------------	--------------------	------------------------

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Haze	5.0 %	5.0 %	ASTM D1003
------	-------	-------	------------

Gloss	70 %	70 %	at 45Å°; ASTM D2457
-------	------	------	---------------------

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Melt Temperature	191 Å°C	375 Å°F	
------------------	---------	---------	--

Descriptive Properties	Value	Comments
------------------------	-------	----------

Antiblock	None	
-----------	------	--

Slip	None	
------	------	--

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China