

## LyondellBasell Pro-fax SB786 Polypropylene Impact Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

### Material Notes:

**Key Features:** blush-resistant, easy molding, high impact polypropylene copolymer resin, good cold impact resistance, good stiffness, FDA acceptable  
**Applications:** automotive battery case, housewares, closures  
**Meets FDA requirements in 21 CFR 177.1520 for all food contact, including cooking applications.**  
**Description:** Pro-fax SB786 easy molding, blush-resistant, high impact polypropylene copolymer resin is available in pellet form. This resin meets FDA requirements in the Code of Federal Regulations in 21 CFR 177.520 for all food contact, including cooking applications. All ingredients meet the chemical registration requirements of TSCA and DSL. It has a UL yellow card RTI, which applies to all colors.  
**Information provided by Montell Polyolefins.** LyondellBasell is the successor company to Montell.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LyondellBasell-Pro-fax-SB786-Polypropylene-Impact-Copolymer.php](http://www.lookpolymers.com/polymer_LyondellBasell-Pro-fax-SB786-Polypropylene-Impact-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in <sup>3</sup>	ASTM D792B
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.0 MPa	3770 psi	ASTM D638
Elongation at Yield	8.0 %	8.0 %	ASTM D638
Flexural Modulus	1.20 GPa	174 ksi	1% secant at 0.05 in/min; ASTM D790A
Izod Impact, Notched	1.00 J/cm	1.87 ft-lb/in	ASTM D256A
Impact Test	29.0 J @Temperature -29.0 °C	21.4 ft-lb @Temperature -20.2 °F	Montell drop weight impact strength

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	87.0 °C	189 °F	ASTM D648
UL RTI, Mechanical with Impact	115 °C	239 °F	Minimum thickness 0.037 inches.
Flammability, UL94	HB	HB	Minimum thickness 0.037 inches.

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China