

M. Holland Company PC406UR Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

High impact resistance Good mold release Good UV resistance High viscosity Applications: Appliances Protective coverings Decorative displays Housings

Order this product through the following link:

http://www.lookpolymers.com/polymer_M-Holland-Company-PC406UR-Polycarbonate.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	23/23Â°C; ASTM D792
Melt Flow	6.0 g/10 min	6.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	72.4 MPa	10500 psi	ASTM D638
Tensile Strength, Yield	60.0 MPa	8700 psi	ASTM D638
Flexural Modulus	2.41 GPa	350 ksi	ASTM D790
Izod Impact, Notched	9.08 J/cm	17.0 ft-lb/in	(0.125 in); ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	142 Â°C	288 Â°F	Annealed; ASTM D648

Descriptive Properties	Value	Comments
Characteristics	Mold release, UV stabilizer	
Forms	Pellets	
Processing Methods	Injection molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China