

MBA Polymers PP 2131 F20 Post-consumer recycled polypropylene copolymer with approximately 20% fillers

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

Available in standard black. Information provided by MBA Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_MBA-Polymers-PP-2131-F20-Post-consumer-recycled-polypropylene-copolymer-with-approximately-20-fillers.php

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in ³	MBA Method
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	24.0 MPa @Temperature 23.0 °C	3480 psi @Temperature 73.4 °F	ISO 527-2/50
Flexural Modulus	2.00 GPa @Temperature 23.0 °C	290 ksi @Temperature 73.4 °F	ISO 178
Izod Impact, Notched (ISO)	4.00 kJ/m ² @Temperature 23.0 °C	1.90 ft-lb/in ² @Temperature 73.4 °F	ISO 180/1A

Processing Properties	Metric	English	Comments
Melt Temperature	180 - 210 °C	356 - 410 °F	Extrusion Range
	200 °C	392 °F	Recommended Extrusion
	200 °C	392 °F	Recommended Injection Molding
	190 - 220 °C	374 - 428 °F	Injection Molding Range
Mold Temperature	40.0 °C	104 °F	Recommended
	30.0 - 60.0 °C	86.0 - 140 °F	
Drying Temperature	80.0 °C @Time 3600 - 7200 sec	176 °F @Time 1.00 - 2.00 hour	

Moisture Content Processing Properties	$\leq 0.10\%$ Metric	$\leq 0.10\%$ English	Comments
---	-------------------------	--------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China