

MRC Polymers MAXTEL,ç 600T10-BK TPO, 10% Talc Filled

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Olefinic Elastomer (TPO)

Material Notes:

For automotive exterior applicationsExcellent process ability and dimensional stabilityCan be UV StabilizedInternal and external lubricants can be addedInformation provided by MRC Polymers Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_MRC-Polymers-MAXTEL-600T10-BK-TPO-10-Talc-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.980 g/cc	0.980 g/cc	ISO 1183
Melt Flow	17 g/10 min @Load 2.16 kg, Temperature 230 Å°C	17 g/10 min @Load 4.76 lb, Temperature 446 Å°F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	58	58	15sec dwell; ISO 868
Tensile Strength, Yield	16.0 MPa	2320 psi	ISO 527
Flexural Strength	22.0 MPa	3190 psi	ISO 178
Flexural Modulus	1.05 GPa	152 ksi	ISO 178
Izod Impact, Notched (ISO)	47.0 kJ/mÅ²	22.4 ft-lb/inÅ²	
Gardner Impact	19.21 J	14.17 ft-lb	ASTM D5420

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	55.0 Å°C @Thickness 3.17 mm	131 Å°F @Thickness 0.125 in	un-annealed; ISO 75

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	182 - 204 Å°C	360 - 400 Å°F	
Middle Barrel Temperature	193 - 216 Å°C	380 - 420 Å°F	
Front Barrel Temperature	204 - 227 Å°C	400 - 440 Å°F	
Nozzle Temperature	216 - 238 Å°C	420 - 460 Å°F	
Melt Temperature	221 - 243 Å°C	430 - 470 Å°F	
Mold Temperature	21.1 - 32.2 Å°C	70.0 - 90.0 Å°F	

Processing Properties	Metric	English	Comments
Dry Time	55.6 A°C 1 - 2 hour	130 A°F 1 - 2 hour	None required
Injection Pressure	48.3 - 55.2 MPa	7000 - 8000 psi	
Back Pressure	0.000 - 1.03 MPa	0.000 - 150 psi	
Cushion	0.635 cm	0.250 in	

Descriptive Properties	Value	Comments
Fill Rate	Slow to Moderate	
Screw Speed	Slow to Moderate	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China